

PLUSHCOLOR™ (APC)

100% Acrylic All Purpose Concentrate for Recreational Surfaces

Model #'s: 32001 (Red), 32002 (Blue), 32003 (Green)

UPC's: Red: 090932320017. Blue: 090932320024. Green: 090932320031

1. MATERIAL DESCRIPTION

PLUSHCOLOR™ RECREATIONAL COATING IS AN ALL PURPOSE CONCENTRATE (APC) that must be mixed with water and/or sand to properly apply. PLUSHCOLOR™ is a top quality all purpose, heavily pigmented, high solid acrylic latex concentrate. It is fortified with fine mineral fillers and acrylic resins. Colorfast pigments product richer, longer lasting, in depth color. PLUSHCOLOR™ produces a greater yield than other systems in that it can be used for the **Finish, Fortified, or Filler Courses**.

2. USES

PLUSHCOLOR™ (APC) serves two purposes:

- a) Use as a **Finish/Top Course** when mixed with the correct amount of clean potable water.
- b) Use as a **Filler/Texture Course** when mixed with correct amounts of silica sand and clean potable water.

3. MATERIAL PROPERTIES

- a) **Colors:** Tournament Green, Tournament Red, Tournament Blue.
- b) **Weight:** 10 lbs./gal.

4. COURT PREPARATION

Prior to applying PLUSHCOLOR (APC), all net posts, sleeves, anchors, and fencing shall be in place. New bituminous concrete pavement shall cure a minimum of 14-28 days prior to application. Concrete shall be allowed to cure for at least 30 days.

5. SURFACE PREPARATION

The surface shall be cleaned removing all loose paint, dirt, dust, mildew, oil, grease, leaves, and other debris or any other foreign matter that may prevent proper bonding. The court surface shall be checked with a ten foot straight edge and/or flooded to locate low areas which are greater than an 1/8" deep. Minor Depressions or "birdbaths" greater than 1/8" – 1/4" shall be identified and repaired. All rough paving joints and roller marks shall be leveled prior to application.

6. MIXING

The mix designs below are for average surfaces. The quantities can be adjusted slightly to achieve specific results and speed of play. Make sure you have empty pails on hand prior to beginning project as you will need to add water per below. To mix properly, split the contents of the pail in half, add ½ of the amount below to each pail to achieve the desired mix.

	(a) As Finish	(b) As Fortified
PLUSHCOLOR™ (APC)	5 gal.	5 gal.
Clean 80-100 mesh Round or angular sand	0	36 lbs.
Clean potable water	1.5 gal.	1.5 gal.

After either water or sand is added to PLUSHCOLOR (APC) thorough mixing is required. A mechanical mixer is recommended and the mixture should be stirred until homogeneous. Periodic mixing is recommended as the application proceeds in order to ensure consistency.

7. COVERAGE

Depending on surface porosity:

- a) **Finish/Top Course** - Approx. 25 sq. yds. of concentrate per gallon per coat (.04 gal. per sq. yd. per coat)
- b) **Fortified (RTU) Ready-To-Use** - Approx. 15 sq. yds. per gallon per coat (.07 gal. per sq. yd. per coat)

8. CLEAN-UP

All equipment can be cleaned with water if clean-up occurs immediately after application.

9. LIMITATIONS

PLUSHCOLOR (APC) should not be applied when ambient temperature is below 50° F or when surface temperature is above 140°F. Do not apply when rain is imminent. Do not store in direct sunlight.

KEEP FROM FREEZING

CAUTION: HARMFUL IF SWALLOWED



10. LIMITATIONS OF WARRANTIES & REMEDIES

Dalton Enterprises, Inc. warrants that this product meets Dalton Enterprises, Inc laboratory specification at point of delivery. Results obtained by the use of Dalton Enterprises, Inc products are dependent upon workmanship and conditions beyond our control. Customers' sole and exclusive remedy for any defective product is limited to replacement of such goods that are defective in manufacture or refund of the purchase price of such goods at Dalton Enterprises, Inc option. Dalton Enterprises, Inc will not be responsible, under any circumstance, for any damages beyond the price of material, including but not limited to, any claims of labor expense or consequential damages that are expressly included. No informal dispute mechanism has been established. Notice must be given in writing to Dalton Enterprises, Inc, 131 Willow Street, Cheshire, CT 06410. A sample of the product claimed defective must be retained together with satisfactory proof of purchase. THIS WARRANTY IS ISSUED AND ACCEPTED IN LIEU OF ALL OTHER EXPRESS OR IMPLIED WARRANTIES AND EXPRESSLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR PARTICULAR PURPOSE, AS WELLAS LIABILITY FOR CONSEQUENTIAL DAMAGES. Dalton Enterprises, Inc. Sales or Technical Representatives have no authority to extend any guarantee beyond that outlined above.

11. FOR FURTHER INFORMATION

Dalton Enterprises, Inc manufactures many different tennis surfacing products. For additional information on **PLUSHCOLOR™ (APC)** or other **PLUSH™** tennis products listed below email info@latexite.com , call 1-888-711-7483, Fax 203-271-3396 or write Dalton Enterprises, Inc, 131 Willow Street, Cheshire, CT 06410, USA.