

TECHNICAL DATA SHEET NATURAL WOOD FIBRE PANELS

(STANDARD CAN/ULC S706)

NATURAL PANEL AND SOUND DEADENING BOARD 1/2"

DESCRIPTION:

The Natural Panel 1/2" or Sound Deadening Board 1/2" is rigid panel produced from non-toxic organic material and natural wood fibres that are wax impregnated. The wax impregnation resists water penetration into the board. The density and rigidity of the board provide excellent noise control properties.

USES:

The panels are used on the interior of frame construction and on interior walls, where it contributes to the absorption of sound transmitted from the exterior or other rooms.

STORAGE:

The wood fibre panels must be stored 100 mm (4") above ground level and adequately protected from the elements with tarpaulins.

| Sizes and Packaging | | | | | | | | | |
|---------------------|-------------------------------|---------------|----------------------------------------------|--|--|--|--|--|--|
| SKU | Dimensions | Panels/Bundle | Coverage/bundle | | | | | | |
| BSNAT85 | 1219 mm x 2438 mm 48"x 96" | 96 | 285.4 m² (3072 ft²) | | | | | | |
| BSNAT8592 | 1219 mm x 2438 mm 48"x 96" | 96 | 285.4 m ² (3072 ft ²) | | | | | | |
| BSNAT85 [] | 1219 mm x 2438 mm 48"x 96" | 96 | 285.4 m ² (3072 ft ²) | | | | | | |

| CHARACTERISTICS | Units | | RESULTS BP | | REQUIREMENTS | | Test Method |
|---------------------------------------------------|--------|----------|------------|----------|--------------|----------|----------------|
| | METRIC | IMPERIAL | METRIC | IMPERIAL | METRIC | IMPERIAL | |
| Nominal Thickness 12.5 mm (0.500'') | % | % | Pass | Pass | +/-10% | +/-10% | ASTM C209 |
| Thermal Resistance min. 25.4 mm (1") | RSI | R | Pass | Pass | 0.41 | 2.43 | ASTM C518 |
| Transverse Load at Rupture, min avg. | N | lbf | Pass | Pass | 55 | 12.4 | ASTM C209 |
| Tensile Strength Parallel to Surface, min avg. | kPa | lb/in² | Pass | Pass | 700 | 101.5 | ASTM C209 |
| Compression Strength at 10% deformation, min avg. | kPa | lb/in² | Pass | Pass | 100 | 14.5 | ASTM C165 |
| Linear Moisture Expansion, max. | % | % | Pass | Pass | 0.5 | 0.5 | ASTM D1037 |
| Water Absorption max.2 hours | % | % | Pass | Pass | 10 | 10 | ASTM C209 |
| Surface Burning Characteristic, max. | FSR | FSR | Pass | Pass | 220 | 220 | ULC S102 |

APPLICABLE STANDARDS

CAN/ULC S706-09, Type I Class 3

Using BP natural panels or sound deadening boards can contribute to qualifying for green building certification programs like LEED[®] audited by Vertima

* Building Products of Canada Corp. has all required documents regarding LEED® and can provide information in a certified project.

Building Products of Canada Inc. 420, rue Dupont Pont-Rouge (Québec), Canada G3H 1S2 www.bpcan.com

TDS-BSNAT85-0.500-23-03-2015