



**VARATHANE®
INTERIOR CLASSIC CLEAR OIL**

DESCRIPTION AND USES

Varathane® Interior Classic Clear Oil is an oil-modified polyurethane designed to provide abrasion and scratch resistance to stained, bare or painted wood surfaces. This product is ideal for application to all interior projects such as furniture, trim, cabinets, toys, wood doors and paneling. It is NOT recommended for linoleum, vinyl or glazed tiles and metal. For wood floors, use Varathane Floor Finishes.

PRODUCTS

SKU	Description
242171H	1-Quart Gloss
242174H	1-Quart Semi-Gloss
242177H	1-Quart Satin

PRODUCT APPLICATION

SURFACE PREPARATION

Previously Finished Surfaces – To ensure proper adhesion, surfaces must be clean, dry, and free of old finishes, dust, dirt, oils or other foreign matter. Old finishes in poor condition should be removed. Sand using 150-220 grit sandpaper to obtain a smooth surface. Remove all sanding dust using a vacuum, tack cloth, or cloth dampened with mineral spirits.

Unfinished Surfaces – Sand using 150-220 grit sandpaper and remove all sanding dust using a vacuum, tack cloth, or rag dampened with mineral spirits. If a filler or putty is used, make sure it does not contain wax allow enough time for it to dry thoroughly.

Stained or Painted Wood – Follow manufacturer’s directions for application of the stain or paint. Make certain the surface is thoroughly dry before applying Varathane Interior Classic Clear Oil. Refer to the manufacturer’s label for dry times. For best results, use Varathane Premium Wood Stains.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

PRODUCT APPLICATION (cont.)

APPLICATION

Use with adequate ventilation at all times. Apply at temperatures are between 55-90°F (13-32°C) and relative humidity is below 85%. Slower dry times may result from applications on redwood, cedar or woods with high oil content, or when applied over stains or sealer or periods of high humidity and/or low temperatures. Use full strength. Do not thin. To prevent bubbles in the finish, do not over-brush, shake or apply with a roller. Interior classic Clear Oil has a slight amber cast.

Stir thoroughly before and during use.. To prevent bubbles in the finish, **DO NOT SHAKE**. Apply using a good quality natural bristle brush or applicator. Allow the finish to dry 4 hours and then recoat. Lower temperatures and/or higher humidity may cause slower dry times. Recoat only when previous coats have dried clear and feel hard. The coating should no longer feel tacky to the touch. If any coat has dried more than 12 hours, lightly sand before re-coating. A minimum of 3 coats is recommended. Allow the finish to dry 24 hours before light use. Wait 3 days before subjecting the surface to normal usage.

APPLICATION TIPS

Test Varathane Interior Classic Clear Oil in an inconspicuous area before beginning. **Testing is particularly important when applying over paints or stains as the appearance of these products may change when an oil-based finish is applied.**

DRY AND RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 1-2 hours and can be recoated in 4-6 hours. Surface is ready for light use in 24 hours and full use in 72 hours.

CLEAN UP

Clean application tools and equipment with mineral spirits or paint thinner.

**TECHNICAL DATA****VARATHANE® INTERIOR CLASSIC CLEAR OIL****PHYSICAL PROPERTIES**

		INTERIOR CLASSIC CLEAR OIL
Resin Type		Oil Modified Urethane
Pigment Type		NA
Solvents		Parachlorobenzotrifluoride, Mineral Spirits
Weight	Per Gallon	8.9-9.0 lbs.
	Per Liter	1.04-1.07 kg
Solids	By Weight	41.3-46.6%
	By Volume	42.3-47.5%
Volatile Organic Compounds		<275 g/l (2.30 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		1.0-1.5 mils (25-37.5µ)
Wet Film to Achieve DFT (unthinned material)		2.0-3.0 mils (50-100µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		100-125 sq.ft./quart (2.5-3.0 m ² /l)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	4 hours
	Handle	4 hours
	Recoat	8 hours
	Full Cure	7 days
Shelf Life		3 years
Flash Point		105°F (40°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877-385-8155
www.rustoleum.com

Form: GDH-865
Rev.: 060215