



**VARATHANE®
AMBER POLYURETHANE SPRAY**

DESCRIPTION AND USES

Varathane® Amber Polyurethane Spray is designed to provide excellent scratch and stain resistance as well as fast dry times in an aerosol. It is recommended for all interior surfaces including furniture, trim, cabinets and doors. Featuring an advance spray system, Varathane Polyurethane can be sprayed at any angle, even upside down for those hard to reach areas. A comfort tip reduces finger fatigue caused by continuous spraying. It is not recommended for floors or items to be used outdoors.

PRODUCTS

SKU	Description
266236	11 ounce Gloss Spray
266237	11 ounce Semi-Gloss Spray
266238	11 ounce Satin Spray

PRODUCT APPLICATION

REFURBISHING

Existing finished wood may be refurbished without complete removal of previous coatings. After using furniture polishes for many years, wood can absorb contaminants that interfere with adhesion of Varathane Polyurethane. To ensure proper adhesion, surfaces must be clean, dry and free of wax, silicones, oils or other contaminants.

SURFACE PREPARATION

Surfaces must be clean, dry and free from wax, grease and dust. Sand area smooth, using 150-220 grit sandpaper. Vacuum the surface to remove dust. Wipe the surface with a clean, lint-free cloth.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

STAINING

For best results, use Varathane Wood Stains prior to using Varathane Polyurethane. For other stains, follow stain manufacturer's recommendations for dry times. Apply Varathane Polyurethane directly over thoroughly cured stain. Test a sample for product compatibility.

APPLICATION

Use adequate ventilation at all times. Do not apply in direct sunlight. Apply only when air (ambient) temperature are between 55-90°F (13-32°C) and the relative humidity is below 85%. Be careful when applying over white or pastel paints or stains as discoloration may occur. Test Varathane Polyurethane in an inconspicuous area before beginning.

Shake the can vigorously before and during use. Use a drop cloth or newspapers to protect surrounding areas from spray mist. Apply light mist coats, holding can 10-12" from the surface and spray with a smooth sweeping motion to avoid runs and sags. Several light coats provides for a better finish than one heavy coat. Allow the finish to dry, then recoat. Dries to the touch in 1 hour and can be recoated after 2 hours. Let dry overnight before use. To ensure a smooth finish, sand lightly between coats using 220 grit sandpaper. For maximum durability, a minimum of 3 coats are recommended.

DRY AND RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 1 hour and can be recoated in 2 hours. Allow 24 hours before full use.

CLEAN UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into the valve opening.

**TECHNICAL DATA****VARATHANE® AMBER POLYURETHANE SPRAY****PHYSICAL PROPERTIES**

Physical Properties		AMBER POLYURETHANE SPRAY
Resin Type		Oil Modified Urethane
Pigment Type		NA
Solvents		Acetone, Mineral Spirits
MIR		1.0 Max
Fill Weight		11 ounces
Recommended Dry Film Thickness (DFT) Per Coat		1.0-1.5 mils (25-37.5 μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		40-50 sq.ft./can (3.7-4.6 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	1 hour
	Handle	1 hour
	Recoat	2 hours
	Full Cure	7 days
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.