

• TRUSTED QUALITY SINCE 1921 •

RUST-OLEUM®
SPECIALTY

**RUST-OLEUM® SPECIALTY
STAINLESS STEEL PAINT**

DESCRIPTION AND USES

Rust-Oleum® Specialty Stainless Steel paint contains stainless steel pigments to provide a rich, metallic finish. The finish is suitable for refinishing the exterior of appliances, such as refrigerators, dishwashers and other household items such as tabletops, picture frames, home accessories and more.

PRODUCTS

SKU	Description
247963	Stainless Steel

PRODUCT APPLICATION

PAINTING CONDITIONS

Apply when temperature is between 50- 90°F (10-32°C) and humidity is below 85% to ensure proper drying. Not intended for continuous water submersion or for surfaces that when heated, exceed 200°F (93°C). Do not use on objects exposed to heat such as stovetops, oven interiors, etc.

SURFACE PREPARATION

Clean the surface with a mild detergent or soap and water, rinse and let dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Remove dust and debris with a vacuum or clean, lint-free rag.

Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. LEAD IS TOXIC. Contact the U.S.EPA/Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Use of Rust-Oleum® primer is recommended for bare wood and metal to provide adhesion and hiding. Recommended primers include Stops Rust® 7780830 Clean Metal primer for metal and Painter's Touch® 1980502 Gray Primer for wood. A primer is not recommended for appliances.

PRODUCT APPLICATION (cont.)

APPLICATION

Mix thoroughly to ensure any settled pigment is re-dispersed before application. Thin the material 5-10% with mineral spirits or acetone if necessary. For large surfaces use a good quality foam roller designed for a smooth finish. For small areas, use a good quality brush. Apply light, even coats to ensure even flow and finish. For a glossy finish, top coat with a Rust-Oleum® Stops Rust® 7701830 Crystal Clear Spray after the paint is fully dry. For plastic surfaces, prime first with Rust-Oleum® Specialty 209460 White Primer Spray.

DRY TIMES

Dry times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 2-4 hours and to handle in 5-9 hours. A second coat may be applied within 1 hour or after 24 hours. One coat is fully dry in 24 hours.

COVERAGE

One quart of Stainless Steel Paint is designed to cover an average size, light colored refrigerator in two coats.

CLEAN-UP

Clean the roller and other application tools with mineral spirits.

TECHNICAL DATA

RUST-OLEUM® SPECIALTY – STAINLESS STEEL PAINT

		STAINLESS STEEL PAINT
Resin Type		Epoxy Ester
Pigment Type		Stainless Steel Flake
Solvents		Glycol Ethers and Mineral Spirits
Weight	Per Gallon	8.65 lbs.
	Per Liter	1.04 kg
Solids	By Weight	50.7%
	By Volume	34.1%
Volatile Organic Compounds		511 g/l
Recommended Dry Film Thickness (DFT) Per Coat		1.5-2.5 mils (37.5-62.5µ)
Wet Film to Achieve DFT (unthinned material)		4.5-7.5 mils (112.5-187.5µ)
Theoretical Coverage at 1 mil DFT (25µ)		137 sq.ft./quart (3.4 m ² /l)
Practical Coverage at Recommended DFT (assumes 15% material loss)		120 sq.ft./quart for 2 coats
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	2-4 hours
	Handle	5-9 hours
	Recoat	Within 1 hour or after 24 hours
	Fully Dry	24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		>93°F (34°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.