



BEHR PREMIUM® Low-Lustre Enamel Porch & Patio Floor Paint

- Resists Scuffing, Fading, Cracking and Peeling
- Mildew Resistant Finish
- 100% Acrylic Latex
- Low-Lustre Sheen

No. 6050-N Ultra Pure White®
No. 6300 Deep Base
No. 6694 Silver Gray
No. 6695 Slate Gray



Spread Rate:
Rough 18-28 m²
Smooth 28-37 m²



Dry Time:
1 Hr. Dry to Touch
4-6 Hr. Recoat



Clean-Up:
Soap & Water



Protect
from Freezing

CAUTION: Painted surfaces may become slippery when wet.
Follow all label instructions.

WHERE TO USE

On properly prepared, previously painted or primed Interior/Exterior surfaces. Ideal for Porches, Floors, Decks, Basement Floors, Patios, Siding, Trim, Furniture and Trellises. **Do not use on areas subject to automotive tires.**

PREPARATION†

(Proper surface preparation is required.) All surfaces must be clean, sound, dry and free of any dirt, oil and grease. Remove mildew stains with a mildew stain removing product. **New or Weathered Wood:** Use a product such as BEHR PREMIUM® No. 63 All-In-One Wood Cleaner. Lightly sand to remove remaining wood fibers/fuzz. **Painted Surfaces-Wood:** For a painted surface in sound condition, use a product such as BEHR PREMIUM No. 63 All-In-One Wood Cleaner, to clean and prepare the surface. If the coating is failing or peeling, use a paint stripper such as BEHR PREMIUM No. 64 Wood Stain & Finish Stripper, to remove old coating. Scuff sand glossy surfaces. Follow with BEHR PREMIUM No. 63 All-In-One Wood Cleaner. Use stainless steel or galvanized nails to prevent nail staining. Countersink nail heads, repair imperfections and sand smooth. Remove all dust with a damp cloth, allow to dry. **Uncoated Concrete or Masonry Surfaces:** Allow new surfaces to cure 30 days. Clean and etch surface using a product such as BEHR PREMIUM No. 991 Concrete & Masonry Cleaner & Etcher to achieve a textured profile similar to 150 grit sandpaper. **Painted Surfaces-Concrete:** For a painted surface in sound condition, use a product such as BEHR PREMIUM No. 990 Concrete & Masonry Degreaser & Cleaner to clean and prepare the surface. If the coating is failing or peeling, use a paint stripper such as BEHR PREMIUM No. 992 Concrete & Masonry Paint Stripper to remove old coating or scrape/sand down to a sound concrete surface. Scuff sand glossy surfaces. Clean and spot etch any exposed concrete using a product such as a BEHR PREMIUM No. 991 Concrete & Masonry Cleaner & Etcher. Remove all dust with a damp cloth, allow to dry.

LIMITED WARRANTY If this product is found to be defective upon inspection by an expert, Behr Process Corporation will, at its option, and upon presentation of proof-of-purchase (the original receipt), either furnish an equivalent amount of new product or refund the original purchase price of this product to you. This warranty is not transferable. If you believe this product is defective, contact Behr Process Corporation at 2750 Centre Avenue N.E., Calgary, AB T2A2L3. The cost of transportation or shipping, if any, are to be assumed by the consumer. The clause of limitation of liability which follows is inapplicable in Quebec: **This warranty excludes (1) labour and costs of labour for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory.** The above provisions are not intended to operate where prohibited by law. This limited warranty is the only warranty provided by Behr Process Corporation unless extended by a provincial consumer statute.

To consult with a Behr Certified Coatings Professional, call 1-800-661-1591.

PRIME

Interior Wood: Use a product such as BEHR PREMIUM PLUS® No. 75 All-In-One Primer & Sealer. **Exterior Wood:** Use a product such as BEHR PREMIUM PLUS No. 436 Multi-Surface Primer & Sealer. **Interior/Exterior Concrete or Masonry:** Over uncoated surfaces, use a product such as BEHR PREMIUM No. 880 Concrete & Masonry Bonding Primer.

APPLICATION

Use product when the surface and air temperatures are between 50 - 90° F (10 - 32° C). Stir paint occasionally. When working with more than one can of the same product, intermix to ensure colour uniformity. Use a high quality 10-13 mm nap roller cover, nylon/polyester brush or an airless sprayer (.015 - .021" spray tip, 60 mesh filter). Spread rate varies, depending on the surface texture, porosity and application method. Additional coats may be required for optimal hide and durability. Do not thin if using a roller or brush; however, if using a sprayer and thinning is required, thin with water at a rate of no more than 250 mL per 3.79 L.

DRY TIME

Longer dry time required in cooler temperatures and in higher humidity. Allow 72 hours before subjecting to normal use. After 30 days, cured paint film may be cleaned with a mild, non-abrasive liquid detergent. Dry paint film is mildew resistant.

DISPOSAL

Properly dispose of all soiled rags. For disposal of empty containers and unused product, contact your household refuse collection service.

† **WARNING!** If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact the National Lead Information Center at 1-800-424-LEAD or log on to www.epa.gov/lead

CAUTION! IRRITANT! HARMFUL IF SWALLOWED. MAY IRRITATE EYES AND SKIN. Avoid contact with eyes, skin and clothing. Do not breathe fumes. Wear eye protection and protective clothing. Use only with adequate ventilation. **FIRST AID TREATMENT:** If swallowed, call a Poison Control Centre or doctor immediately. Do not induce vomiting. If in eyes rinse with water for 20 minutes. If on skin rinse well with water. If inhaled, move person to fresh air.

CAUTION: KEEP OUT OF REACH OF CHILDREN - DO NOT TAKE INTERNALLY.

BEHR
A Masco Company

©2016 Behr Process Corporation
Santa Ana, CA 92704 U.S.A. • behr.com
V.O.C. (C.O.V.) <50 g/L • REV. 08/16