



PORCH & PATIO FLOOR PAINT
NO. 6705 (GLOSS) ULTRA PURE WHITE®



PRODUCT INFORMATION

BEHR PREMIUM® Porch & Patio Floor Paint is made of 100% acrylic latex, has a mildew resistant finish, and is available in two sheens, Low-Lustre and Gloss Enamel. Resists scuffing, fading, cracking and peeling while providing a durable, long-lasting finish that is ideal for both interior and exterior applications.

RECOMMENDED USES:

This product is ideal for porches, floors, decks, basements, patios, siding, trim, furniture and trellises. Not for use on garage floors or areas subject to automotive traffic. Use on previously painted or primed interior or exterior surfaces such as:

- Wood
- Concrete
- Composite

PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint Load:

- No. 6705 128 oz. /2 oz.
- No. 6740 120 oz. /10 oz.
- No. 6730 116 oz. /14 oz.

PRE-MIXED COLORS:

- No. 6794 Gloss Silver Gray
- No. 6795 Gloss Slate Gray

Gloss: 65+ @ 60°

Resin Type: 100% Acrylic Latex

Weight per Gallon: 10.5 lbs.

% Solids by Volume: 34.4%

% Solids by Weight: 47.7%

VOC: <100 g/L

Flash Point: N/A

Viscosity: 95-100 KU

Recommended Film Thickness:

- Wet: 8.0 Dry: 2.8 mils @ 200 Sq. Ft./Gal.
- Wet: 4.0 Dry: 1.4 mils @ 400 Sq. Ft./Gal.

Coverage: 200-400 Sq. Ft./Gal. depending on application method and substrate porosity. Does not include the loss of material from spraying.

APPLICATION:

Brush: Nylon/polyester

Roller: 3/8"-1/2" nap

Airless Spray: At packaged consistency

Tip: .015" - .019"

Filter: 60 mesh

Thinning: (If required) No more than 1/2 pint of water per gallon.

Dry Time: @ 77° & 50% RH

Longer dry time may be required in cooler temperatures and higher humidity.

To Touch: 1 hour

To Recoat: 4-6 hours

Full Cure: 2 weeks (UPW base); 4 weeks (Medium and Deep base). Allow 72 hours before subjecting to normal use. After 4 weeks, wood paint film may be cleansed with a mild, non-abrasive liquid detergent.

SURFACE PREPARATION:

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust and all other foreign substances.

Non-Ferrous Metal: The oil film on new non-ferrous metal must be removed before it is painted. Remove oil film with a detergent and water solution. For better paint adhesion, sand the surface with sandpaper, steel wool, or by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. **New Surfaces:** Wipe down clean metal surfaces prior to painting with a vinegar solution, one part vinegar to five parts water (1:5). Bare metal must be primed the same day it is cleaned.

Metal: Remove all rust and mill scale using sandpaper, steel wool, abrasive blasting, or other abrading methods to create a profile on the metal's surface. Clean the metal by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Bare metal must be coated the same day it is cleaned.

Vinyl Siding, Architectural Plastics: Previously Painted Surface: Remove loose paint and all other foreign substances. Clean any dirt by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. For best results, apply a primer such as PREMIUM PLUS® Exterior Multi-Surface Primer & Sealer No. 436 prior to topcoat application. **CAUTION:** Vinyl siding is manufactured to withstand certain levels of heat intensity. Be sure when choosing a paint color, to select a color which is similar or lighter than the vinyl siding's original color. A darker color paint will absorb more heat, resulting in a warping of the siding.

COMPLIES WITH THE BELOW AS OF 9/1/2014			
CARB	YES	AIM	YES
OTC	YES	LEED v.3 (2009)†	YES
LADCO	YES		

†Please visit www.usgbc.org/LEED for additional details.

Wood: Shakes & Shingles, Composition Panels/ Siding, Fiber Board: New Wood: Remove mill glaze with sandpaper or use a product such as BEHR PREMIUM® All-in-One Wood Cleaner No. 63 to open the pores of the wood and follow all label instructions. Remove mildew stains with a mildew stain removing product. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking and allow to dry completely. Patched and filled surfaces should be sanded smooth and dusted clean prior to coating. **Previously Painted Wood:** Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely prior to coating. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating. **Weathered Wood Surfaces:** To remove loose wood fibers, latex, oil-based and 100% acrylic coatings on new or weathered wood decks, siding, fences, shakes and shingles, use a product such as BEHR PREMIUM® Wood Stain & Finish Stripper No. 64 and follow all label instructions. Use a product such as BEHR PREMIUM All-in-One Wood Cleaner No. 63 and follow all label instructions to clean and brighten the wood surface and to remove light to medium stains caused by mold, mildew, algae and fungus. Be sure to follow all label instructions.

Wood: WARNING! Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

Tannin Bleed & Stainblocking: After priming, test for stain bleed-through by applying the topcoat to a small section. If the stain bleeds through the topcoat, apply a second coat of primer and test again before top-coating the entire area. If bleeding continues, a longer dry time of the primer may be needed before top-coating or an additional coat of primer may be required to block the tannin bleed or stain.





PORCH & PATIO FLOOR PAINT

NO. 6705 (GLOSS) ULTRA PURE WHITE®

Masonry: Stucco, Concrete, Cut Masonry Unit's (CMUs),

Split-Faced Block: New: All masonry surfaces must be cured at least 30 days before painting. The pH must be 10.0 or lower prior to coating. Smooth masonry may require an adequate profile for adhesion. For all other smooth concrete, create a profile using mechanical means.

Masonry: Cement Composition Panels/Siding, Exterior Insulation and Finish Systems (EIFS) or Synthetic Stucco: New:

All masonry surfaces must be cured at least 30 days before painting. The pH must be 10.0 or lower prior to coating. All surfaces must be clean, free of dust, chalk, mold and mildew stains, loose and peeling paint and all other foreign substances. Clean surfaces with a detergent and water solution by scrubbing the surface vigorously and rinse with a garden hose or a power washer at a low setting (500-1200 PSI). **DO NOT USE HIGH PRESSURE** as this may harm the substrate. **Previously Painted Surface:** All surfaces must be clean, free of dust, chalk, mold and mildew stains, loose and peeling paint and all other foreign substances. Clean surfaces with a detergent and water solution by scrubbing the surface vigorously and rinse with a garden hose or a power washer and allow to dry.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact the National Lead Information Center at 1-800-424-LEAD or log on to www.epa.gov/lead.

RECOMMENDED PRIMER/SYSTEMS:

PROPERLY PREPARED NEW SURFACES:

Wood:

- BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436
- BEHR PREMIUM PLUS Interior All-In-One Primer & Sealer No. 75

Tannin/Stainblocking:

- BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436
- For Interior Tannin/Stainblocking: BEHR PREMIUM PLUS Interior All-In-One Primer & Sealer No. 75

Masonry:

- BEHR PREMIUM Concrete & Masonry Bonding Primer No. 880
- BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436
- BEHR PREMIUM PLUS Interior All-In-One Primer & Sealer No. 75

Masonry with pH Levels up to 13.0:

- BEHR PREMIUM Interior/Exterior Basement & Masonry Waterproofing No. 875
- BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

Non-Ferrous Metal:

- BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

Vinyl Siding, Architectural Plastics:

- BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

CLEAN UP:

Clean all tools and equipment with clean water. For disposal of empty containers and unused product, contact your household refuse collection service.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- Do not use on garage floors and driveways.
- Do not use on roofs.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying too fast. Avoid painting in direct sun. NOTE: If the surface is hot to the touch it should be considered too hot to apply this coating.
- Allow 72 hours before subjecting to normal use.
- After 30 days, cured paint film may be cleaned with a mild, non-abrasive liquid detergent.
- Shelf life under normal conditions is two years unopened.

GENERAL INFORMATION:



Warning! Causes eye and skin irritation. Harmful if swallowed. Wear protective clothing, gloves, eye, and face protection. Do not eat, drink, or smoke when using this product. Take off contaminated clothing and wash it before reuse. Wash hands thoroughly after handling. Collect spillage and avoid release to the environment. Dispose of unused, contents, container and other contaminated wastes in accordance with local, state, federal and provincial regulations.

First aid: If in eyes: Rinse cautiously with water for several minutes and remove contacts if present and easy to do. Continue rinsing and get medical attention if eye irritation persists. **If on skin:** Wash with plenty of soap and water. **If swallowed:** Rinse mouth and get medical attention if you feel unwell.