

• TRUSTED QUALITY SINCE 1921 •

**RUST-OLEUM®**  
SPECIALTY

**SPECIALTY  
APPLIANCE TOUCH-UP PAINT**

**DESCRIPTION AND USES**

Rust-Oleum® Specialty Appliance Touch-Up Paint is a quick dry lacquer designed to provide a long-lasting, high gloss finish on repairs to metal, porcelain, and appliances such as stoves, refrigerators, washers, dryers and dishwashers. This washable, moisture resistant finish is designed for the exteriors of these surfaces. Do not use on surfaces exposed to temperatures over 200°F (93°C) such as stove tops. Not for use in sinks, tubs or other water immersed surfaces.

**PRODUCTS**

SKU (0.6 ounces)	Description
203000	White
203001	Almond
203002	Biscuit
213174	Black

**PRODUCT APPLICATION**

**PAINTING CONDITIONS**

Use when air and surface temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C).

**SURFACE PREPARATION**

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Clean with soap and water, rinse and let dry.

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you sand, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRODUCT APPLICATION (CONT.)**

**APPLICATION**

Shake bottle to mix product. Unscrew the cap brush and apply Appliance Touch-Up Epoxy using even strokes. For deep scratches or chips, apply multiple layers allowing 10 minutes between coats. For best results, allow to dry overnight before use. **Do not use near open flame.**

**DRY and RECOAT TIMES**

Based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 10 minutes, to handle in 30 minutes and is fully dry in 24 hours. Allow to dry 10 minutes between coats.

**CLEAN-UP**

Clean up any excess product with lacquer thinner, rubbing alcohol or acetone.

**TECHNICAL DATA**  
**SPECIALTY APPLIANCE TOUCH-UP PAINT**

**PHYSICAL PROPERTIES**

		APPLIANCE TOUCH-UP PAINT
<b>Resin Type</b>		Acrylic Lacquer
<b>Pigment Type</b>		Varies with color
<b>Solvents</b>		Mineral Spirits, 2-Propanol, 1-Methoxy Acetate, Toluene
<b>Weight</b>	<b>Per Gallon</b>	8.2-9.3 lbs.
	<b>Per Liter</b>	1.0-1.1 kg
<b>Solids</b>	<b>By Weight</b>	28.1-36.7%
	<b>By Volume</b>	22.6-23.0%
<b>Volatile Organic Compounds</b>		<710 g/l (5.90 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) per Coat</b>		2.0-4.0 mils (50-100µ)
<b>Wet Film to Achieve DFT (unthinned material)</b>		9.0-18.0 mils (225-450µ)
<b>Theoretical Coverage at 1mil DFT (25µ)</b>		1.7 sq.ft./bottle (0.6 ounces)
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		0.25-0.5 sq.ft./bottle (0.6 ounces)
<b>Dry Times at 70-80°F (21°-27C) and 50% Relative Humidity</b>	<b>Touch</b>	10 minutes
	<b>Handle</b>	30 minutes
	<b>Recoat</b>	Allow 10 minutes between coats
<b>Dry Heat Resistance</b>		200°F (93°C)
<b>Shelf Life</b>		3 years
<b>Flash Point</b>		57F (14°C)
<b>Safety Information</b>		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.