



# ALL WEATHER BLACKTOP PATCH

◆ The Pro's Choice Since 1936



Sakrete® All Weather Blacktop Patch is a ready to use asphalt repair product designed for the permanent repair of potholes, large cracks and other defects in asphalt surfaces. Repairs can be opened to traffic immediately after proper compaction. The unique design provides an environmentally friendly low VOC product.

**Maximum repair area is not to exceed 2' x 2' x 4" (0.6 m x 0.6 m x 103 mm).**

### Features:

- Environmentally preferable - VOC compliant
- Easy to use - does not require heating
- Fast and permanent
- Minimum 2-year shelf life

### Use For:

- Patch and repair potholes in blacktop walks, driveways and parking lots

### Yield/Coverage:

Per 60 lb (27.2 kg) bag:

Area in ft <sup>2</sup> (m <sup>2</sup> )	3 (0.3)	4 (0.4)
1" (25 mm) deep	1	1
2" (51 mm) deep	2	2
3" (75 mm) deep	2	3
4" (102 mm) deep	3	4

### Color:

Black

### Preparation:

- Chisel out loose blacktop. Try to avoid a bird bath shaped hole. Sweep clean removing all debris. A hose can be used to wash out loose material.
- Pour a 2" (51 mm) layer of All Weather Blacktop Patch into the pot hole. Compact into a 1" (25 mm) layer using a tamper or 4" x 4" (103 x 103 mm) post. Place and compact additional layers until the hole is filled.
- Finished repair should be mounded slightly higher than the surrounding asphalt surface.
- Very high summer temperatures can cause freshly applied material to track. Placing sand on the repair will minimize tracking.

### Placement and Compaction:

Pour a 2" (51 mm) layer of loose All Weather Blacktop Patch into the area to be patched. Level the loose material and then compact to a 1" (51 mm) layer. Compact with a tamper or a 4" x 4" (103 x 103 mm) post. **PLACE AND COMPACT**

additional layers until desired thickness is achieved. Riding over the patch with a car will not provide sufficient compaction. Compaction must be sufficient to cause the stone in the blacktop to lock together and minimize voids in each layer. If the blacktop is not completely compacted, the patch will remain soft and the material may not stay in place. Properly compacted All Weather Blacktop Patch will continue to harden over time.

### Tips for use:

All Weather Blacktop Patch may be opened to traffic immediately after being thoroughly compacted. Under certain conditions the surface may remain tacky for a short period of time. If this occurs, a light layer of sand may be helpful. Do not apply driveway sealer to the patched area for a period of 60-90 days of warm weather.

*NOTE: Proper application and installation of all Sakrete products are the responsibility of the end user.*

### Safety:

READ and UNDERSTAND the Safety Data Sheet (SDS) before using this product. **WARNING:** Wear protective clothing and equipment. For emergency information, call CHEMTREC at 800-424-9300 or 703-527-3887 (outside USA).

**KEEP OUT OF REACH OF CHILDREN.**

### Limited Product Warranty:

The manufacturer warrants that this product shall be of merchantable quality when used or applied in accordance with the manufacturer's instructions. This product is not warranted as suitable for any purpose other than the general purpose for which it is intended. This warranty runs for one (1) year from the dates the product is purchased. ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ON THIS PRODUCT IS LIMITED TO THE DURATION OF THIS WARRANTY. Liability under this warranty is limited to replacement or defective products or, at the manufacturer's option, refund of the purchase price. **CONSEQUENTIAL AND INCIDENTAL DAMAGES ARE NOT RECOVERABLE UNDER THIS WARRANTY.**

