TECHNICAL FILE







The Earthen oxide, Oxidized gray, Misty white and Quarz sand finishes have been lacquered, obtaining so a high quality and homogeneus surface. The lacquering has the quality seal Qualicoat, which guarantees the quality of the process and the final products.

Aluminum has excellent chemical, physical and mechanical properties. It is lightweight, tough, ductile, malleable and highly durable.

Installation

Stair nosing

- 1. Spread a big amount of thin-set mortar on the surface of the riser.
- 2. Place tiles on the riser and press them to get an optimal adherence.
- 3. Then, spread a big amount of thin-set mortar on the tread and align the profile to its vertex so it rests on the riser (Do not let overhang, the leverage may remove the step and the tiles). Then press it to let the thin-set mortar pass through the holes of the anchoring wing.
- 4. Place a tile on the tread, align it to the profile and press them to get a perfect adhesion. You can tap it softly with a rubber hammer.
- 5. Clean the possible leftover material and let dry.

As a finish (countertops, windowsills...)

If you want to install Novoperi as a finishing and you don't want to tile the front part of the installation, just follow the instructions detailed above and obviate the two first steps.

Cleaning and maintenance

The cleaning must be done periodically with a soft cloth. If you use a neutral liquid cleaner, you must rinse the profile with cold water and dry to remove excess moisture. If dirtiness persists, clean the profile with a solution with clean water and detergent or neutral soap 5%, brushing with a cloth that has no particles that could scracht the finish. Ensure the lacquered surface is totally cold (maximum 20°C) before the cleaning.

Steel wool, abrasive cleaners, souring products as well as strong acids (hydrochloric and perchloric), strong bases (caustic soda or ammonia) or carbonated solutions are not recommended. Citric acid is neither recommended because disolves the protective layer of the surface of aluminium. Waxes, petrolatum, lanolin or similar substances are not appropriate. Solvents containing haloalkanes (hydrofluoroether and chlorinated solvents) and curing accelerators containing chlorides should not be used (use special accelerators free of chlorides).

Technical information

You can find out more information about the technical features of Emac®'s products by downloading its Technical File in **www.emac.es**.

If you have any query, please contact our Technical Department in **tecnico@emac.es**.









Emac Complementos S.L. (Spain) info@emac.es // Emac America L.L.C. (FL,USA) info@emac-america.com // Emac Italia S.R.L. (Italy) info@emac-italia.it www.emac.es