



TECHNICAL DATA

AAC-10

AMERICAN ACCENTS DISTRESSED IVORY KIT

DESCRIPTION AND USES

Rust-Oleum® American Accents® Distressed Ivory Kit is designed to add antique quality to bare wood and previously painted wood, as well as metal, plaster, masonry and unglazed ceramics. It is suitable for interior use or for use in a covered outdoor location. This easy 2-step process does not require priming.

PRODUCTS

The Kit includes:

Ivory Base Coat (211827)
Antique Top Coat (260508)
Sanding Pad
Gloves
Paint Brush

PRODUCT APPLICATION

PAINTING CONDITIONS

Apply only when the ambient air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with soap and water, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand previously painted or glossy surfaces with the enclosed sanding pad to improve paint adhesion. Wipe with a soft cloth or tack cloth to remove sanding dust. **WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact the U.S.EPA/Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

BASE COAT APPLICATION

Wear the enclosed gloves. Stir thoroughly to ensure any settled pigment is re-dispersed. Thinning is not required. In hot, dry conditions, thin with up to 2 ounces of water per quart to extend dry time. Avoid painting in direct sunlight or on hot surfaces. Using the enclosed brush, apply the base coat using even strokes. For wooden objects, always brush in the direction of the wood grain. Avoid excessive brushing. Two coats may be necessary depending on the original color of the object. Once the base coat is thoroughly dry (2 hours), the object is ready to distress and apply the antique top coat.

DISTRESSING THE SURFACE

Use the enclosed sanding pad to sand (distress) areas that would be naturally worn, such as edges, raised areas, and corners. Always sand in the direction of the grain of the wood. When sanding is complete, wipe down with a soft cloth or tack cloth to remove sanding dust.

ANTIQUÉ TOP COAT APPLICATION

Stir gently before and during application. **DO NOT SHAKE.** Do not apply below 55°F (13°C). Put on the enclosed gloves. Using the enclosed brush, apply liberally to the work area no larger than 2 square feet. Immediately after applying the stain, wipe with a damp cloth. The stain will stay in the exposed wood areas. For a heavier or more distressed effect, wipe the stain immediately with a dry cloth. More stain can be applied and wiped off to achieve the desired look. Dries to the touch in 15 minutes.

For extra protection on heavily used surfaces such as table tops or outdoor objects, top coat with American Accents® Matte Clear. Allow the object to dry overnight before applying the Matte Clear.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. The base coat dries to touch in 30 minutes, and may be recoated in 2-4 hours. The antique top coat dries to the touch in 15 minutes and is fully dry in 24 hours.

CLEAN-UP

Clean brush and other application tools immediately with soap and water.

TECHNICAL DATA

AMERICAN ACCENTS DISTRESSED IVORY KIT

		IVORY BASE COAT	ANTIQUE TOP COAT
Resin Type		Water-based Acrylic	Water-based Acrylic
Pigment Type		Titanium dioxide, Iron oxides	Iron oxides, Carbon black
Solvents		Water, Propylene Glycol, Texanol	Water, Glycol ethers, Propylene glycol
Weight	Per Gallon	12.4 lbs.	8.7 lbs.
	Per Liter	1.48 kg	1.04 kg
Solids	By Weight	61.3%	21.4%
	By Volume	42.6%	18.4%
Volatile Organic Compounds		<250 g/l 2.08 lbs./gal.	<150 g/l 1.25 lbs./gal.
Recommended Dry Film Thickness (DFT) per Coat		1.5 – 2.5 mils (37.5-62.5μ)	1.5 – 2.5 mils (37.5-62.5μ)
Wet Film to Achieve DFT (unthinned material)		3.5-6.0 mils (87.5-150μ)	8.0-13.5 mils (200-337.5μ)
Theoretical Coverage at 1 mil DFT (25μ)		683 sq.ft./gal.	295 sq.ft./gal.
Practical Coverage at Recommended DFT (assumes 15% material loss)		1 Kit covers 60-85 square feet	1 kit covers 60-85 square feet
Dry Times at 70°F (21°C) and 50% Relative Humidity	Touch	30 minutes	15 minutes
	Recoat	2-4 hours	NA
	Fully Dry	NA	24 hours
Shelf Life		5 years	5 years
Flash Point		>200°F (93°C)	>200°F (93°C)
Safety Information		For additional information, see MSDS.	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.