



STOPS RUST RUST INHIBITOR

DESCRIPTION AND USES

Rust-Oleum® Rust Inhibitor is a clear coating that protects untreated, bare metal surfaces against moisture and other corrosive elements. It is suitable for use on garden tools, bicycles, metal sporting equipment, lawn equipment, iron railings and other metal surfaces.

PRODUCTS

SKU (10.25 fl. oz.)	Description
224284	Rust Inhibitor

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove all loose rust, scale, and previous coatings with a wire brush, scraper, or Rust-Oleum® Rust Stripper. **WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Apply when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure efficient use of the product. Do not apply to an area that, when heated, will exceed 120°F (49°C). Avoid spraying in windy, dusty conditions. Cover surrounding area to protect from spray mist.

APPLICATION

Shake can well before using and often during use. Hold can upright 12-16" from the surface and apply a light, thin, even coat to cover the surface. Additional coats provide increased protection. Wipe off excess with a clean cloth if the coating is too heavy. Re-apply every 1-2 years for indoor uses and every 6 months for outdoor uses.

PAINTING

If surfaces are to be painted in the future, remove Rust Inhibitor from the surface with a solvent such as acetone or mineral spirits prior to painting.



TECHNICAL DATA

STOPS RUST – RUST INHIBITOR

PHYSICAL PROPERTIES

Physical Properties	RUST INHIBITOR
Composition	Petroleum Distillates
Fill Weight	10.25 ounces
VOC	325 g/l
Shelf Life	1 year from date of manufacture
Flash Point	-156°F (-104°C)
Safety Information	For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877-385-8155
www.rustoleum.com

Form: GDH-09
Rev.: 030613