

# CEMENT ALL

Multi-Purpose Repair Material & Non-Shrink Grout



## PRODUCT DATASHEET

**DESCRIPTION:** Rapid Set® CEMENT ALL® is a high-performance, fast-setting, multi-purpose concrete repair material and non-shrink grout. Durable in wet environments, CEMENT ALL is a blend of Rapid Set hydraulic cement and specially graded fine aggregates. CEMENT ALL is non-metallic and no chlorides are added. Mix CEMENT ALL with water to produce a workable, high quality material that is ideal where rapid strength gain and high durability are desired. CEMENT ALL sets in 15 minutes and achieves structural strength in 1 hour.\*

**USES:** Use CEMENT ALL for general and structural concrete repair, doweling and anchoring, industrial grouting, formed work, vertical and horizontal trowel applications. CEMENT ALL is ideal for airport, highway, industrial and marine applications.

**ENVIRONMENTAL ADVANTAGES:** Use CEMENT ALL to reduce your carbon footprint and lower your environmental impact. Production of Rapid Set cement emits far less CO<sub>2</sub> than portland cement. Contact your representative for LEED values and environmental information.

**APPLICATION:** Apply CEMENT ALL in thicknesses from featheredge to 4" (10 cm). For heavy loads and vehicle traffic, minimum thickness will vary. Not intended for high heat applications above 300°F (149°C). For deeper sections, use Rapid Set® Mortar Mix or Rapid Set® Concrete Mix. For overlay applications, a minimum of one test section should be prepared to evaluate the suitability of the materials and procedures.

**SURFACE PREPARATION:** For repairs, application surface must be clean, sound and free from any materials that may inhibit bond, such as oil, asphalt, curing compound, acid, dirt and loose debris. Roughen surface and remove all unsound material. Apply CEMENT ALL to a surface that is thoroughly saturated with no standing water.

**MIXING:** The use of a power-driven mechanical mixer, such as a mortar mixer or a drill-mounted mixer, is recommended. Organize work so that all personnel and equipment are in place before mixing. Use clean potable water. **CEMENT ALL may be mixed using 3 to 5 quarts (2.8 L to 4.7 L) of water per 55-lb (25-kg) bag. Use less water to achieve higher strengths. Do not exceed 5 quarts (4.7 L) of water per bag.** For increased fluidity and workability, use Rapid Set® FLOW Control® plasticizing admixture from the Rapid Set® Concrete Pharmacy®. Place the desired quantity of mix water into the mixing container. While the mixer is running, add CEMENT ALL. Mix for the minimum amount of time required to achieve a lump-free, uniform consistency (usually 1 to 3 minutes). Do not retemper.

**PLACEMENT:** CEMENT ALL may be placed using traditional construction methods. Organize work so that all personnel and equipment are ready before placement. Place, consolidate and screed quickly to allow for maximum finishing time. Use a method of consolidation that eliminates air voids. Do not wait for bleed water; apply final finish as soon as possible. CEMENT ALL may be troweled, floated or broom finished. On flat work, do not install in layers. Install full-depth sections and progress horizontally. Do not install on frozen surfaces. To extend working time, use Rapid Set® SET Control® retarding admixture from the Concrete Pharmacy or cold mix water. CEMENT ALL may be applied in temperatures ranging from 45°F to 90°F (7°C to 32°C).

## OVERVIEW

### Highlights:

**Fast:** Sets in 15 minutes, structural strength in 1 hour\*

**Durable:** Formulated for long life in critical applications

**Excellent Bond:** Superior adhesion to concrete, stone, brick, block, stucco and more

**Structural:** For repair and new construction

**Multi-Purpose:** Use for concrete repair, grouting, anchoring, casting, underlayment and more

### Conforms to:

ASTM: C1107, C928, C387 and CRD C621

Army Corps of Engineers

LA Research and Report 24654

State and Local Approvals

### MasterFormat® 2016

03 01 30 Maintenance of Cast-in-Place Concrete

03 01 40 Maintenance of Precast Concrete

03 01 60 Maintenance of Grouting

03 01 70 Maintenance of Mass Concrete

03 53 19 Concrete Overlayment

03 54 16 Hydraulic Cement Underlayment

03 60 00 Grouting

03 61 00 Cementitious Grouting

03 62 13 Non-Metallic Non-Shrink Grouting

04 01 00 Maintenance of Masonry

### Manufacturer:

CTS Cement Manufacturing Corp.

12442 Knott St.

Garden Grove, CA 92841

Tel: 800-929-3030 | Fax: 714-379-8270

Web: [www.CTScement.com](http://www.CTScement.com)

E-mail: [info@CTScement.com](mailto:info@CTScement.com)



# CEMENT ALL Multi-Purpose Repair Material & Non-Shrink Grout

**CURING:** Water cure all Rapid Set® CEMENT ALL® installations by keeping exposed surfaces wet for a minimum of 1 hour. Begin curing as soon as the surface starts to lose its moist sheen. When experiencing extended setting time due to cold temperature or the use of retarder, longer curing times may be required. The objective of water curing shall be to maintain a continuously wet surface until the product has achieved sufficient strength.

**COLD WEATHER:** Environmental and material temperatures below 70°F (21°C) may delay setting time and reduce the rate of strength gain. Lower temperatures will have a more pronounced effect. Thinner sections will be more significantly affected. To compensate for cold temperatures, keep material warm, use heated mix water, and follow ACI 306 Procedures for Cold Weather Concreting.

**WARM WEATHER:** Environmental and material temperatures above 70°F (21°C) may speed setting time and increase the rate of strength gain. Higher temperatures will have a more pronounced effect. To compensate for warm temperatures, keep material cool, use chilled mix water, and follow ACI 305 Procedures for Hot Weather Concreting. The use of Rapid Set® SET Control retarding admixture from the Rapid Set® Concrete Pharmacy will help offset the effects of high temperatures.

**YIELD & PACKAGING:** CEMENT ALL is available in 55-lb, 25-lb and 10-lb (25-kg, 11.3-kg and 4.5-kg) sizes. One 55-lb (25-kg) bag of CEMENT ALL will yield approximately 0.5 ft<sup>3</sup>.

**SHELF LIFE:** CEMENT ALL has a shelf life of 12 months when stored properly in a dry location, protected from moisture, out of direct sunlight, and in an undamaged package.

**USER RESPONSIBILITY:** Before using CTS products, read current technical data sheets, bulletins, product labels and safety data sheets at [www.CTScement.com](http://www.CTScement.com). It is the user's responsibility to review instructions and warnings for any CTS products prior to use.

**WARNING: DO NOT BREATHE DUST. AVOID CONTACT WITH SKIN AND EYES.** Use material in well-ventilated areas only. Exposure to cement dust may irritate eyes, nose, throat, and the upper respiratory system/lungs. Silica exposure by inhalation may result in the development of lung injuries and pulmonary diseases, including silicosis and lung cancer. Seek medical treatment if you experience difficulty breathing while using this product. The use of a NIOSH/MSHA-approved respirator (P-, N- or R-95) is recommended to minimize inhalation of cement dust. Eat and drink only in dust-free areas to avoid ingesting cement dust. Skin contact with dry material or wet mixtures may result in bodily injury ranging from moderate irritation and thickening/cracking of skin to severe skin damage from chemical burns. If irritation or burning occurs, seek medical treatment. Protect eyes with goggles or safety glasses with side shields. Cover skin with protective clothing. Use chemical resistant gloves and waterproof boots. In case of skin contact with cement dust, immediately wash off dust with soap and water to avoid skin damage. In case of skin contact with wet concrete, wash exposed skin areas with cold running water as soon as possible. In case of eye contact with cement dust, flush immediately and repeatedly with clean water, and consult a physician. If wet concrete splashes into eyes, rinse eyes with clean water for at least 15 minutes and go to the hospital for further treatment.

Please refer to the SDS and [www.CTScement.com](http://www.CTScement.com) for additional safety information regarding this material.

**LIMITED WARRANTY:** CTS CEMENT MANUFACTURING CORP. (CTS) warrants its materials to be of good quality and, at its option, will replace or refund the purchase price of any material proven to be defective within one (1) year from date of purchase. The above remedies shall be the limit of CTS's responsibility. Except for the foregoing, all warranties expressed or implied, including merchantability and fitness for a particular purpose, are excluded. CTS shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the materials.

**⚠ WARNING**  
CANCER and REPRODUCTIVE HARM - [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

## TYPICAL PHYSICAL DATA

### Set Time, ASTM C191 Mod.

Initial set	15 minutes
Final set	35 minutes

### Compressive Strength, ASTM C109 Mod.

1 hour*	3000 psi (20.7 MPa)
3 hours	5000 psi (34.5 MPa)
24 hours	6000 psi (41.4 MPa)
7 days	7000 psi (48.3 MPa)
28 days	9000 psi (62.1 MPa)

### Slant Shear Bond, ASTM C882 per C928

24 hours	1500 psi (10.3 MPa)
28 days	2500 psi (17.2 MPa)

### Splitting Tensile, ASTM C496

7 days	700 psi (4.82 MPa)
28 days	880 psi (6.06 MPa)

### Flexural Strength, ASTM C78

7 days	600 psi (4.14 MPa)
28 days	800 psi (5.51 MPa)

\*After final set  
Data obtained at flow consistency 102 by ASTM C1437  
All data produced at 70°F (21°C)



USGBC and related logo is a trademark owned by the U.S. Green Building Council and is used by permission.