



**PRO FINISHER
POLYURETHANE 275 VOC**

DESCRIPTION AND USES

Pro Finisher Polyurethane 275 VOC is a traditional wood floor finish that meets the stringent requirements of all states that enforce a 275 VOC regulation. This professional grade polyurethane is recommended for all wood floors and all other interior wood surfaces where a fast drying beautiful protective finish is required. Pro Finisher Polyurethane provides a warm, slightly ambered clear coating that accents the richness of wood flooring. The finish will darken somewhat with time and exposure to sunlight.

PRODUCTS

| SKU (1-Gallon) | Description |
|----------------|-------------|
| 330813 | Gloss |
| 330833 | Semi-Gloss |
| 330823 | Satin |

SURFACE PREPARATION

Surfaces must be clean, dry, and free of wax, grease, oil, shellac, lacquer, mildew, and polishes.

SANDING SURFACE:

Sand area smooth, progressing in sandpaper grit from rough to medium to fine. For hardwood floors, use NOFMA and NHFA accepted methods or see Pro Finisher Professional Finishing Techniques for sanding details. After sanding vacuum surface and wipe with a cloth to remove all dust.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

STAINING SURFACE:

Oil or water based stains can be used prior to finish application for custom coloring. Allow stain to dry thoroughly. Test a sample area for product compatibility. If applying stain, do not use a sanding sealer before staining. Oil-Base finish may be applied directly over thoroughly dry stain.

SEALING SURFACE:

A sanding sealer may be used as an option to initially coat bare wood surface. It penetrates and seals the wood and dries quickly. Pro Finisher Universal Sealer is recommended because of its excellent adhesion and extremely fast dry time. Sealer must be completely dry before applying finish.

SURFACE PREPARATION (cont.)

REFURBISH PREFINISHED SURFACE:

If existing finished wood surface or wood floor is in good condition and free from wax or other contaminants, you may recoat without sanding the surface to bare wood. A thorough cleaning and abrading of prefinished surface is required. If compatibility with the old finish is unknown, a sealer coat of Pro Finisher Universal Sealer will minimize potential adhesion problems.

PRODUCT APPLICATION

Stir contents before using and frequently during use. Do not shake container. Apply Pro Finisher Polyurethane Finish using a synthetic or Lambswool applicator pad, natural bristle brush, polyester brush, short nap roller or weighted T-bar. Apply in direction of wood grain in smooth, level strokes. Apply thin, even coats at a rate of 350-450 square feet per gallon. Allow product to dry 8-10 hours until film is totally dry. Environmental conditions or heavy application of finish may extend dry times. Heavy application of finish is not recommended. After first coat has dried, abrade the surface using 120 to 150 grit sandpaper. Vacuum and wipe clean. Follow this procedure for successive coats. Sanding between coats is not required for intercoat adhesion as long as the timeline between coats does not exceed 15 hours. Sanding between coats produces a smooth, better looking job. A minimum of 2-3 coats is recommended. Allow final coat to dry overnight before permitting use of surface. Finish will take up to 30 days to completely cure. Do not place area rugs on floor, and avoid exposure to washing and heavy traffic for a minimum of 2 weeks.

COVERAGE

Varies with surface porosity and will cover approximately 400 square feet per gallon.

DRY TIME

Dry times are based on 70°F and 50% relative humidity. Pro Finisher Polyurethane 275 VOC dries to the touch in 4-5 hours and can be recoated in 8-10 hours. Full cure will be reached in 30 days.

CLEAN-UP

Clean application tools and equipment with mineral spirits or paint thinner.

**TECHNICAL DATA****PRO FINISHER POLYURETHANE 275 VOC****PHYSICAL PROPERTIES**

| | | OIL BASE POLYURETHANE 275 VOC |
|--|-------------------|---|
| Resin Type | | Oil Modified Polyurethane |
| Pigments | | NA |
| Solvents | | Mineral Spirits |
| Weight | Per Gallon | 8.7-8.9 lbs. |
| | Per Liter | 1.04-1.07 kg |
| Solids | By Weight | 40.1-41.4% |
| | By Volume | 41.7-42.1% |
| Volatile Organic Compounds | | 275 g/l (2.29 lbs./gal.) |
| Recommended Dry Film Thickness (DFT) per Coat | | 1.5 mils (37.5 μ) |
| Wet Film to Achieve DFT (unthinned material) | | 3.5 mils (87.5 μ) |
| Theoretical Coverage at 1 mil DFT (25μ) | | 675 sq.ft./gal. (16.6 m ² /l) |
| Practical Coverage at Recommended DFT (assumes 15% material loss) | | 400 sq.ft./gal. (9.8 m ² /l) Varies with surface porosity |
| Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity | Touch | 4-5 hours |
| | Recoat | 8-10 hours |
| | Dry to use | 14-18 hours (overnight) |
| Shelf Life | | 3 years |
| Flash Point | | 93°F (34°C) |
| Safety Information | | For additional information, see SDS |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.