



**WATCO®
DANISH OIL FINISH (275 VOC)**

DESCRIPTION AND USES

Watco® Danish Oil Finish is a unique blend of penetrating oil & varnish that stains, seals and protects in one easy step. Danish Oil penetrates deep into wood pores to protect from within and to enhance the natural look of the wood. It creates the rich, warm glow of a traditional hand-rubbed finish. Danish Oil will not chip, peel or wear away. Danish Oil is recommended for furniture, trim, molding or any bare wood interior surface. It is not recommended for floors or exterior surfaces. Danish Oil is easy to use. Simply brush or wipe on and wipe off.

FEATURES

- Stains, seals & protects
- Penetrates deeply
- Easy, wipe-on application

PRODUCTS

SKU	Description
242217	Natural 1-Gallon
242222	Medium Walnut 1-Gallon
265500	Dark Walnut 1-Pint
265502	Natural 1-Pint
265504	Medium Walnut 1-Pint
265507	Cherry 1-Pint
242211H	Golden Oak 1-Pint
242731H	Fruitwood 1-Pint

PRODUCT APPLICATION

SURFACE PREPARATION

Ensure the wood is dry and that all previous coatings such as paint or varnish are completely removed. Sand wood smooth and wipe clean.

WARNING! If you scrape, sand or remove old paint, you may Release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake container thoroughly and test for color on a hidden section of wood. **NOTE:** To ensure uniform color and/or appearance, complete the entire project with the same stain color as shown on the label. Flood the surface with a brush or cloth, applying additional finish to areas that absorb all of the liquid. Allow to penetrate for 30 minutes. Re-apply allowing an additional 15 minutes penetration. Wipe the surface completely dry. The surface is ready for use in 8-10 hours.

If a topcoat such as a polyurethane is desired, allow Watco Danish Oil to dry 72 hours before application of the polyurethane.

MAINTENANCE

Apply fresh coats as needed to repair surface scratches and remove minor stains. Burnish affected area with fine steel wool or 220 grit sandpaper. Then apply the color of Watco Danish Oil originally used to finish the wood.

CLEAN UP

Clean application tools and equipment with mineral spirits or paint thinner.

OPTIONAL STEPS

Pre-treat soft woods such as pine by lightly wiping the wood surface with a cloth dampened with Danish Oil Finish in Natural. Immediately wipe the surface completely dry and apply the Danish Oil Finish in your color of choice. If a clear wood finish such as polyurethane is desired, use Varathane Interior Premium Polyurethane or Varathane Professional Polyurethane.

NOTE: Dry time varies with temperature, humidity and ventilation.

**TECHNICAL DATA****WAT-15****WATCO® DANISH OIL FINISH (275 VOC)****PHYSICAL PROPERTIES**

		DANISH OIL FINISH
Resin Type		Raw Linseed Oil, Soybean Oil, Hydrocarbon Resin
Pigment Type		None
Solvents		Mineral Spirits, Light Aromatic Naphtha
Weight	Per Gallon	7.5-7.8 lbs.
	Per Liter	0.90-0.94 kg
Solids	By Weight	64.8-65.1%
	By Volume	59.4-61.2%
Volatile Organic Compounds		<275 g/l (2.30 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		1.0-1.5 mils (25-37.5µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		550-600 sq.ft./gal. (16.0-18.5 m ² /l) Varies with type and porosity of wood
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Penetrate	30 minutes
	Reapply	15 minutes
	Light Use	8-10 hours
	Topcoat	If polyurethane is desired, wait 72 hours
Shelf Life		3 years
Flash Point		104°F (40°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.