




Novosepara 1 Aluminium



Novosepara 1 Aluminium is a made of aluminium profile designed to be installed as a flooring separator. Its sides are striated to improve the grip between the profile and the flooring. It can be installed during the tiling work or once it is finished, with high thickness floorings such as terrazzo, marble... It can be polished.

General Features



Material:	Aluminium
Length:	2,5 lm
Dimensions:	a: 4 mm h:30 mm
Finishes:	Natural

Applications

Novosepara 1 is a profile designed as a flooring separator for high thickness floorings such as terrazzo, marble, etc

Technical Features

Alloy:	6063 (AA y ASTM) L-3441 (UNE 38-301-89)
Fire resistance:	M0 (UNE 23-727-90)
Abrasion resistance:	High
Lightfastness:	Excellent
Appearance and color:	EN 12373-1

Materials

Aluminium

Novosepara 1 is a profile made by aluminium extrusion.

The aluminum is a raw material with excellent chemical and physicomechanical properties. It is light, tough, ductile, malleable and highly durable. It has a great resistance to fire and corrosion.

Installation

Novosepara 1 Aluminio is a easy to install profile.

1. Do the tiling until the place to install the Novosepara 1
2. Apply thin-set mortar and place the profile aligning it with the side of the floor
3. Continue with the tiling
4. Remove the possible leftover material and let dry

Alternatively, you can install the flooring leaving the gap for the Novosepara 1. Then, spread thin-set mortar or mounting adhesive inside and insert the profile into the gap.

Cleaning and maintenance

The product must be cleaned periodically with a soft cloth. If you use a neutral liquid cleaner, you must rinse the profile with cold water and dry it to remove the humidity excess. The persistent dirtiness can be removed by using cleaning approved agents lightly abrasive or a grid covered with polished powder neutral.

Steel wool, abrasive cleaners, souring products as well as strong acids (hydrochloric and perchloric), strong bases (caustic soda or ammonia) or carbonated solutions are not recommended. Citric acid is neither recommended because it dissolves the protective layer of the surface of aluminium. Waxes, petrolatum, lanolin or similar substances are not appropriate. Solvents containing haloalkanes (hydrofluoroether and chlorinated solvents) and curing accelerators containing chlorides should not be used (use special accelerators free of chlorides).

Technical information

You can find out more information about the technical features of Emac®'s products by downloading its Technical File in www.emac.es.

If you have any query, please contact our Technical Department in tecnico@emac.es.

