

Carriff Corporation's Soil Separator Specifications

SPECIFICATION	Test Method	Soil Separator	
Fiber		Polyester	
Weight (Oz/yd ²) Applied	ASTM D-3776	0.5	
Thickness, in (mm)		0.005	(0.10)
Mullen Burst, p.s.i. (kpa)	ASTM D-3786	20	
Air Permeability ft ³ /ft ² /min(cm ³ /cm ² /sec)	ASTM D-737	800	
Trapezoid Tear	ASTM D-4533	MD	N/A
		XD	N/A
Water Permeability by Permittivity s(-1)	ASTM D-4491	N/A	
AOS, US sieve	ASTM D-4751	20	
AOS, (UM)	ASTM D-4751	840	

