



## VARATHANE® POLYURETHANE FLOOR FINISH (275 VOC)

### DESCRIPTION AND USES

Varathane® Polyurethane Floor Finish is designed to provide the best protection for wood floors, offering excellent scuff and scratch resistance. Varathane Polyurethane Floor Finish is recommended for interior bare wood or stained floors. It is ideal for high traffic areas in kitchens and hallways. It is not recommended for use on linoleum, vinyl, or glazed tiles or metal.

### PRODUCTS

SKU	Description
242606	1-Gallon Gloss
242607	1-Gallon Semi-Gloss
242608	1-Gallon Satin

### PRODUCT APPLICATION

#### SURFACE PREPARATION

#### PREVIOUSLY FINISHED SURFACES

For best adhesion, surfaces must be clean, dry and free of wax, grease, oil, shellac, lacquer, mildew and polishes. Waxes must be removed with a wax stripper; sanding does not remove wax. Shellac must be removed with a paint stripper. Previously finished floors in good condition should be cleaned with a TSP (Tri Sodium Phosphate) solution in water, and rinsed thoroughly with clean water. Do not use TSP on bare wood floors as discoloring will occur. Some types of prefinished or factory finished floors may not be compatible with Varathane Polyurethane Floor Finish. Old finishes in poor condition must be removed. Use the Varathane EZV® floor sander to obtain a smooth surface. Remove all sanding dust using a vacuum or cloth dampened with mineral spirits. **Warning: Sanding dust can be a spontaneous combustion hazard. Always dispose of collected sanding dust immediately.**

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

#### STAINED OR PAINTED WOOD

Follow manufacturer's directions for application of stain or paint. Make certain surface is thoroughly dry before applying Varathane Premium Floor Finish. Refer to manufacturer's label for dry times. For best results, use Varathane Premium Wood Stains.

### PRODUCT APPLICATION (Cont.)

#### UNFINISHED SURFACE PREPARATION

Using the Varathane EZV sander, sand the new wood surface. Remove dust with a rag dampened with mineral spirits or with a vacuum.

#### APPLICATION

Use adequate ventilation at all times. Apply when temperatures are between 55-90°F (12-38°C) and the relative humidity is below 85%. Slower dry times may result from applications on redwood, cedar or woods with a high oil content, or when applied over stains or sealers, or periods of high humidity and/or low temperatures Do not dilute. To prevent bubbles in the finish, do not over-brush, shake or apply with a roller.

Stir thoroughly before and during use. To prevent bubbles in the finish, **DO NOT SHAKE**. Apply using a good quality, natural bristle brush or wool applicator. Allow finish to dry a minimum of 12 hours and then recoat. Lower temperatures and/or higher humidity may cause slower dry times. Recoat only when previous coats have dried clear and feel hard and are no longer tacky to the touch. Lightly sand before recoating. Apply additional coats following directions above. A total of 2 coats are recommended. Allow finish to dry 24 hours before light use. Wait 3 days before subjecting surface to normal usage.

#### APPLICATION TIPS

Test Varathane Polyurethane Floor Finish in an inconspicuous area before beginning. **Testing is particularly important when applying over paints or stains as the appearance of these products may change when an oil-based finish is applied.**

#### DRY AND RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 2-4 hours and can be recoated in 12 hours. Surface is ready for light foot traffic in 24 hours and full use in 3 days.

#### CLEAN-UP

For easy project clean-up, use paint thinner or mineral spirits. Dispose of properly. For disposal guidance of unused amounts, contact your local, state or government environmental control agency.

**COVERAGE:** 500-600 square feet/gallon.



**TECHNICAL DATA**  
**VARATHANE® POLYURETHANE FLOOR FINISH (275 VOC)**

**PHYSICAL PROPERTIES**

		POLYURETHANE FLOOR FINISH
<b>Resin Type</b>		Oil Modified Urethane
<b>Pigment Type</b>		NA
<b>Solvents</b>		Parachlorobenzotrifluoride, Mineral Spirits
<b>Weight</b>	<b>Per Gallon</b>	8.4-9.1lbs.
	<b>Per Liter</b>	1.00-1.09 kg
<b>Solids</b>	<b>By Weight</b>	42.4-45.5%
	<b>By Volume</b>	43.7-44.0%
<b>Volatile Organic Compounds</b>		275 g/l (2.30 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		1.0-1.5 mils (25µ)
<b>Wet Film to Achieve DFT (unthinned material)</b>		2.0-3.5 mils (50-87.5µ)
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		400-500 sq.ft./gal. (9.9-12.3 m <sup>2</sup> /l)
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Touch</b>	4 hours
	<b>Handle</b>	8 hours
	<b>Recoat</b>	12 hours
	<b>Full Cure</b>	7 days
<b>Shelf Life</b>		3 years
<b>Flash Point</b>		105° F (40°C)
<b>Safety Information</b>		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
 11 Hawthorn Parkway  
 Vernon Hills, Illinois 60061  
 An RPM Company

Phone: 877-385-8155  
[www.rustoleum.com](http://www.rustoleum.com)

Form: GDH-862  
 Rev.: 060215