PEEL COAT®
TOP COAT EFFECTS – GLOSS CLEAR

DESCRIPTION AND USES

Rust-Oleum® Peel Coat® Gloss Clear is a clear topcoat that transforms any Peel Coat matte finish into a glossy shine. Peel Coat is a removable rubber coating that provides endless customization for automotive and other applications. Peel Coat is suitable for use on metal, plastic and more.

NOTE: ONLY APPLY PEEL COAT TOP COAT EFFECTS COLOR SHIFT OVER BLACK PEEL COAT. NOT INTENDED FORUSE OVER ANY OTHER PRODUCTS OR SURFACES.

PRODUCTS

SKU	Description
297343	Gloss Clear

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Thoroughly wash Peel Coat base coat with soap and water prior to application. Rinse with fresh water and allow to dry.

PRODUCT APPLICATION   (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Mask off the area to be coated. Make sure the Peel Coat color is completely dry before top coating. Hold can 8-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Apply as many coats as desired. The last coat should be applied as a wet coat to ensure the coating lays smoothly on the surface. Remove any tape while the last coat is still wet. Allow coating to dry 5 minutes between coats. Allow the coating to cure for 24 hours before washing. The topcoat alone cannot be removed. If desired, the topcoat and base coat color are removed together. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes and can be handled in 1 hour.

REMOVAL

You can peel film off once the coating has fully cured. A microfiber cloth or mineral spirits may assist in the removal of film in intricate areas. The original base coat color and topcoat will be removed together. This coating has been formulated for temporary use and is recommended to be removed within 6 months or less.

CLEAN-UP

When finished spraying, clear the spray valve by turning can upside down and pushing the button for 5 seconds. Allow wet paint to dry and once dry. Once dry, peel away or clean up with mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

PHYSICAL PROPERTIES

		PEEL COAT TOP COAT EFFECTS – GLOSS CLEAR
Resin Type		Synthetic Rubber
Pigment Type		None
Solvents		Blend of Aliphatic and Aromatic Solvents
MIR		1.60 Max
Fill Weight		10 ounces
Recommended Dry Film Thickness (DFT) Per Coat		0.5-1.0 mils (12.5-25µ)
Practical Coverage at Recommended DFT		7.5 sq.ft./can (0.70 m^2/can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	**Touch**	20 minutes
	Handle	1 hour
	Recoat	20 minutes
Shelf Life		2 years
Flash Point		-140°F (-96°C)
Safety Information		For additional information, see SDS