



**EXTERIOR SATIN ENAMEL PAINT**  
**NO. 9450 ULTRA PURE WHITE®**



**PRODUCT INFORMATION**

BEHR MARQUEE® Stain Blocking Paint & primer delivers remarkable dirt and fade resistance for exterior application. Provides a tough, non-stick surface helping to prevent dirt adhesion, while UV protection technology delivers longer lasting color. The paint film is also able to resist rain as early as 60 minutes after application. Exterior finishes will look freshly painted longer, even under the most challenging weather conditions.

**RECOMMENDED USES:**

Use on properly prepared, primed or previously painted exterior surfaces such as:

- Concrete
- Cement Board Siding
- Brick
- Stucco
- Wood
- Plywood
- Ferrous Metals
- Non-Ferrous Metals

Note: Chalky substrates must be thoroughly cleaned to remove all chalk by pressure washing or other suitable methods. All loose & peeling paint must be removed prior to painting or priming.

**PRODUCT SPECIFICATIONS:**

**Tint Bases/Max Tint Load:**

- No. 9450 128 oz. / 2 o.z
- No. 9454 120 oz. / 10 oz.
- No. 9453 116 oz. / 14 oz.

**Gloss:** 15-25 @ 60°

**Sheen:** >35 @ 85°

**Resin Type:** 100% Acrylic Latex

**Weight per Gallon:** 10.2 lbs.

**% Solids by Volume:** 38%

**% Solids by Weight:** 48.5%

**VOC:** <50 g/L

**Flash Point:** N/A

**Viscosity:** 100-110 KU

**Recommended Film Thickness:**

- Wet: 6.4 mils / Dry: 2.4 mils @ 250 Sq. Ft./Gal.
- Wet: 4.0 mils / Dry: 1.5 mils @ 400 Sq. Ft./Gal.

**Coverage:** 250-400 Sq. Ft./Gal. depending on application method and substrate porosity. Does not include the loss of material from spraying.

**APPLICATION:**

**Brush:** Nylon/polyester

**Roller:**

- Smooth Surface:** 3/8" - 1/2" nap
- Rough Surface:** 1/2" - 3/4" nap

**Airless Spray:** At packaged consistency

**Tip:** .015" - .021"

**Filter:** 60 mesh

**Thinning:** (If required) No more than 1/2 pint of water per gallon.

**Dry Time:** @ 77° & 50% RH

**To Touch:** 1 hour

**To Recoat:** 2 hours (3 hours for deep base)

**Full Cure:** 4 weeks

**SURFACE PREPARATION:**

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust, and all other foreign substances.

**New Drywall:** All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating. **Previously Painted Drywall:** Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating.

**New Wood:** Remove mill glaze with sand paper. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Previously Painted Wood:** Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all

COMPLIES WITH THE BELOW AS OF 6/1/2016			
SCAQMD	YES	LEED v.4 <sup>†</sup>	YES
CARB	YES	MPI#	15,315
OTC	YES	GREENGUARD	YES
LADCO	YES	CHPS	YES
AIM	YES	NAHB/ICC NGBS	YES
LEED v.3 (2009) <sup>†</sup>	YES		

<sup>†</sup>Please visit [www.usgbc.org/LEED](http://www.usgbc.org/LEED) for additional details.

dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating.

**Wood: WARNING!** Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

**New Plaster:** New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize. **Previously Painted Plaster:** Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material. Let dry completely and sand smooth. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating.

**Stainblocking:** After priming, test for stain bleed-through by applying the topcoat to a small section. If the stain bleeds through the topcoat, apply a second coat of primer and test again before topcoating the entire area. If bleeding continues, a longer dry time of the primer may be needed before topcoating.

**Masonry:** All masonry surfaces must be cured at least 30 days before painting. The pH must be 10.0 or lower prior to coating. Smooth masonry may require an adequate profile for adhesion. For all other smooth trowel concrete, create a profile using a product such as a muriatic acid etcher or with mechanical means. Remove loose aggregate and debris using a product such as a muriatic acid etcher.



**BEHR**  
**MARQUEE**

## EXTERIOR SATIN ENAMEL PAINT

### NO. 9450 ULTRA PURE WHITE®

**Metals: Ferrous and Non-Ferrous Metals:** All metals should be clean and free of any oils, rust, mill scale or other contaminants. All metals require sufficient “tooth” or profile for optimum adhesion and therefore require some type of sanding, abrasion, or chemical etching. **Oil films:** (especially on new or non-ferrous metals) should be removed by scrubbing the surface with a detergent and water solution, and thoroughly rinsed. **Rust and Mill Scale:** Remove all rust and mill scale using sandpaper, steel wool, abrasive blasting, or other abrading methods. **Profile:** For best adhesion results, sand all metal surfaces (including new ones) with sandpaper, steel wool, or etch using a product such as a muriatic etcher. Clean by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. All ferrous metals must be primed the same day it is cleaned to prevent rust.

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact the National Lead Information Center at 1-800-424-LEAD or visit [www.epa.gov/lead](http://www.epa.gov/lead).

### RECOMMENDED PRIMER/SYSTEMS:

#### PROPERLY PREPARED NEW SURFACES:

**Wood: Cedar, Redwood, Shakes & Shingles;  
For Severe Tannin Bleed/Stainblocking:**

- BEHR PREMIUM PLUS® Interior/Exterior Multi-Surface Primer & Sealer No. 436

**Masonry: Stucco, Cinder Block, Cut Masonry  
Units(CMUs), Split Face Block**

- BEHR PREMIUM Basement & Masonry Waterproofer No. 875

**Masonry: Cement Composition Panels/Siding,  
Exterior Insulation and Finish Systems (EIFS)  
or Synthetic Stucco**

- BEHR PREMIUM Interior/Exterior Basement & Masonry Waterproofer No. 875

**Masonry with pH Levels up to 13.0:**

- BEHR PREMIUM Interior/Exterior Basement & Masonry Waterproofer No. 875
- BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

**Ferrous and Non-Ferrous Metals:**

- BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

### PREVIOUSLY PAINTED SURFACES:

- Use a full coat, or spot prime repaired, or uncoated surfaces, such as woods with heavy tannins (Redwood and Cedar) with BEHR MARQUEE® paint. Two coats may be required.

### TEST SPECIFICATIONS:

#### Scrubability:

ASTM D2486 Scrub > 2500 (no shim)

#### Biological Growth:

ASTM D3273 (4 weeks) – Pass

#### Accelerated Weathering:

ASTM D4587, 500 hrs exposure - Pass

### CLEAN UP:

Clean all tools and equipment with clean water. For disposal of empty containers and unused product, contact your household refuse collection service.

### CAUTIONS/LIMITATIONS:

- Protect from freezing.
- Do not use on floors.
- For best results, apply at temperatures between 35°F - 90°F. Temperatures above 90°F may affect the dry time.
- Avoid heavy traffic for 24 hours.
- Allow four weeks before washing or cleaning for full cure.
- Shelf life under normal conditions is two years unopened.

### GENERAL INFORMATION:



**Warning!** Causes eye and skin irritation. Wear protective clothing, gloves, and eye & face protection. Do not eat, drink, or smoke when using this product. Take off contaminated clothing and wash it before reuse. Wash hands thoroughly after handling. Dispose of unused contents, container and other contaminated wastes in accordance with local, state, federal and provincial regulations.

**First aid: If in eyes:** Rinse cautiously with water for several minutes and remove contacts if present and easy to do. Continue rinsing and get medical attention if eye irritation persists. **If on skin:** Wash with plenty of soap and water. **If swallowed:** Rinse mouth and get medical attention if you feel unwell.

