



Typical Physical Properties ADO Pro Pac

Raw Material: 100% Polypropylene
Type: Point-bond

Characteristic	U.M	Average Value	Tolerance	Test Method
Weight	OSY	1.25	± 10%	ASTM D 3776-96
Thickness	Mil	16	± 10%	EDANA 30.5-99
Tensile Strength M.D.	N/2.54cm	28.10 lbs	± 20%	ASTM D 5034-90
Tensile Strength C.D.	N/2.54cm	24.74 lbs	± 20%	ASTM D 5034-90
Elongation M.D.	%	75	± 20%	ASTM D 5034-90
Elongation C.D.	%	75	± 20%	ASTM D 5034-90
Trapezoid Tear M.D.	N	8.99 lbs	± 20%	ASTM D 5733-95
Trapezoid Tear C.D.	N	11.01 lbs	± 20%	ASTM D 5733-95
Air Permeability	Cfm	450	± 20%	ASTM D 737-96

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for, the accuracy or reliability of said information or the performance of any product. Any specification, properties or applications listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.