

MASONRY CEMENT

PRODUCT NO. 1125-70 (TYPE N), -71 (TYPE S), -72 (TYPE M)

PRODUCT DESCRIPTION

QUIKRETE® Masonry Cement can be used for making Type N, Type S or Type M masonry mortars, and for other applications requiring masonry cement.

PRODUCT USE

QUIKRETE® Masonry Cement complies with current ASTM C91 and Federal Specifications from masonry cement

SIZES

- QUIKRETE® Masonry Cement – 70 lb (31.8 kg) bags

YIELD

• Yield depends on application. A typical mix design consisting of one bag of QUIKRETE® Masonry Cement and 240 pounds of QUIKRETE® Mason Sand will yield approximately 2.75 cu. ft. of mortar and will lay about 46 standard block or 144 standard bricks.

TECHNICAL DATA

QUIKRETE® Masonry Cement complies with ASTM C 91 Type N, S or M as identified.

Typical Mix designs meeting ASTM C270 are as follows:

Type N Mortar Mix:

1 Part QUIKRETE® Masonry Cement T-N (#1125-70)
3 Parts QUIKRETE® Mason Sand(#1952)

Type S Mortar Mix:

1 Part QUIKRETE® Masonry Cement T-S (#1125-71)
3 Parts QUIKRETE® Mason Sand (#1952)

Type M Mortar Mix:

1 Part QUIKRETE® Masonry Cement T-M (#1125-72)
3 Parts QUIKRETE® Mason Sand(#1952)

DIVISION 4

Cement
04 05 13



INSTALLATION

SURFACE PREPARATION

Surfaces to receive masonry mortar should be dry or damp and clean and free of dirt loose debris, grease, oil or any other material which would reduce the bond of the mortar to the masonry.

PRECAUTIONS

- Must be blended with the specified amount of properly graded sand meeting ASTM C 144.
- Do not use QUIKRETE® Masonry Cement at temperatures below 40°F (4.4°C) or if the temperature is expected to fall below freezing within 48 hr.

WARRANTY

The QUIKRETE® Companies warrant this product to be of merchantable quality when used or applied in accordance with the instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of its product (as purchased) found to be defective, or at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given to The QUIKRETE® Companies in writing. This limited warranty is issued and accepted in lieu of all other express warranties and expressly excludes liability for consequential damages.

The QUIKRETE® Companies
One Securities Centre
3490 Piedmont Rd., NE, Suite 1300, Atlanta, GA 30305
(404) 634-9100 • Fax: (404) 842-1425

* Refer to www.quikrete.com for the most current technical data, MSDS, and guide specifications