

MARTHA STEWART[™] LIVING METALLIC PAINT

DESCRIPTION AND USES

Rust-Oleum[®] Martha Stewart[™] Living Metallic Paint is an all purpose home decorating finish for walls, furniture and accent pieces.

Metallic Glaze is an all purpose home decorating glaze for use over metallic paint and other painted or unpainted surfaces.

PRODUCTS

10 oz. Jar	Description
259283	Metallic Thundercloud
259284	Metallic Copper Red
259285	Metallic Vintage Gold
259286	Metallic Golden Pearl
259287	Metallic Cast Bronze
259289	Metallic Glaze Black Coffee

PRODUCT APPLICATION

PAINTING CONDITIONS

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.eps.gov/lead.

PRODUCT APPLICATION (cont.)

PRIMING

Use of a latex primer (American Accents 7980502 White Primer) promotes adhesion and enhances hiding and is especially recommended for bare wood, bare metal, new drywall or as a primer over contrasting colors.

APPLICATION

Before using, stir thoroughly to ensure any settled pigment is redispersed. Apply with a brush or a sponge. Metallic Paint is water-based for easy clean-up with soap and water.

NOTE: The paint finish will have a subtle texture. If applying by brush, use a high quality brush recommended for water-based semi-gloss paints.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 30 minutes, dries to handle in 1 hour, and can be recoated in 2-4 hours.

CLEAN-UP

Clean brush and other application tools immediately with soap and water.

Form: GDH-586 Rev.: 112114



TECHNICAL DATA

MARTHA STEWART LIVING METALLIC PAINT

PHYSICAL PROPERTIES

		METALLIC PAINT	METALLIC GLAZE
Resin Type		Water-based Acrylic	Water-based Acrylic
Pigment Type		Varies with color	Titanium dioxide, Carbon Black
Solvents		Water, Glycol Ethers	Water, Glycol Ethers
Weight	Per Gallon	9.3-9.7 lbs.	8.9 lbs.
	Per Liter	1.11-1.16 kg	1.07 kg
Solias	By Weight	33.9-36.7%	18.7%
	By Volume	25.9-27.4%	14.9%
Volatile Organic Compounds		<130 g/l (1.08 lbs./gal.)	<765 g/l (6.36 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5 mils (37.5-62.5µ)	1.0-2.0 mils (25-50µ)
Wet Film to Achieve DFT (unthinned material)		5.5-9.0 mils (137.5-225μ)	7.0-13.0 mils (175-325µ)
Theoretical Coverage at 1 mil DFT (25µ)		32-35 sq.ft./jar (0.8-0.9 m²)	19 sq.ft./jar (0.5 m²l)
Practical Coverage at Recommended DFT (assumes 15% material loss)		12-18 sq.ft./jar (0.3-0.4 m²)	8-15 sq.ft./jar (0.2-0.4m²)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes	30 minutes
	Handle	1 hour	1 hour
	Recoat	2-4 hours	2-4 hours
Shelf Life		3 years	3 years
Flash Point		>180°F (83°C)	200°F (93°C)
Safety Information		For additional information, see MSDS	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Form: GDH-586 Rev.: 112114