

• TRUSTED QUALITY SINCE 1921 •

RUST-OLEUM®
SPECIALTY

GLOW IN THE DARK MAX

DESCRIPTION AND USES

Rust-Oleum® Glow In The Dark MAX is a luminous paint that creates a glowing effect for 4-8 hours in the dark after being charged by natural or artificial light. It can be applied to wood, metal, drywall and plastic. It is suitable for use in bedrooms, craft projects and more. Periodic re-application may be needed for outdoor use. **IMPORTANT! Use over a white or light colored surface.**

FEATURES AND BENEFITS

- Glows two times stronger and brighter than competition
- Great for indoor and outdoor use on functional and decorative projects

PRODUCTS

SKU (10 oz. spray)	Description
278733	Glow In The Dark MAX

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Apply when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Wash the surface with a commercial detergent, or other suitable cleaning method to remove dirt. Rinse with fresh water and dry with a clean cloth. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. **WARNING:** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION

PRIMING

Use of a Rust-Oleum White primer provides added corrosion protection, enhances adhesion and hiding, and is especially recommended for metal and wood surfaces. Recommended primers include 224430T Painters Touch Flat White Primer, 7980502 American Accents Flat White Primer and 249058 Painters Touch White Primer.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Make sure to apply paint to the reverse side of glass that will be displayed. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more coats a few minutes apart. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Dries to the touch in 15 minutes, to handle in 1-2 hours and is fully dry in 24 hours. Apply a second coat or a clear coat (267028) within 1 hour or after 24 hours.

CLEAN-UP

When finished spraying, clear spray valve by turning can upside down and pushing spray button for 5 seconds. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

TECHNICAL DATA

GLOW IN THE DARK MAX

PHYSICAL PROPERTIES

Physical Properties		GLOW IN THE DARK
Resin Type		Alkyd Resin Polymer
Pigment Type		Phosphorescent Pigment
MIR		1.30 Max
Fill Weight		10 ounces
Solvents		Acetone, N-Butyl Acetate, Xylene, VM&P Naphtha
Practical Coverage at Recommended DFT (assumes 15% material loss)		8-10 sq.ft./can. (0.7-0.9 m ² /can)
Dry Times at 70°F (21°C) and 50% Relative Humidity	Touch	15 minutes
	Handle	1-2 hours
	Fully Dry	24 hours
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see MSDS.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.