

# KRUD KUTTER<sup>®</sup> RUSTEX<sup>™</sup> RUST CONVERTER

## **DESCRIPTION AND USES**

Krud Kutter<sup>®</sup> Rustex<sup>™</sup> Rust Converter is a rust inhibiting coating which converts rusted metal overnight into a rust retarding, paintable surface. When applied to rusted surfaces, iron oxide (rust) is chemically changed to iron phosphate, an inert, hard substance that turns the metal black. This increases the paint adhesion, and durability of the coating.

## **PRODUCTS**

SKU	Description
RX326	32 ounce Bottle
RX012	1-Gallon Bottle

## PRODUCT APPLICATION

#### **DIRECTIONS**

IMPORTANT - READ ENTIRE LABEL BEFORE USE

- Do not use when temperature is below 36°F.
   Excessive dew and humidity may prolong drying time and cause powdery buildup.
- Do not use an airless sprayer or dilute this product.
- Spray equipment should be flushed out with water after use. Clean brushes with water.
- Avoid getting product on adjacent areas such as painted surfaces, concrete, masonry and stonework. If splashing occurs, flush immediately with water to remove.
- DO NOT MIX THIS PRODUCT WITH ANY OTHER CHEMICALS.
- Do not mix this product with any other chemicals.

## PRODUCT APPLICATION (cont.)

#### **DIRECTIONS - RUSTED & OLD METAL:**

For heavily soiled surfaces use the Original Krud Kutter to remove excess oil, grease and dirt. Remove loose paint and heavy rust with a wire brush. Light rust need not be removed. Apply directly to metal by brush, roller, mop, or low-pressure sprayer. Heavy rust may need two applications. Wait overnight after application, dust off any loose powder, and apply undercoat primer and paint. Test small area for compatibility when using epoxy or latex paint.

#### **DIRECTIONS-GALVANIZED:**

Apply one coat, and let stand for 30-60 minutes or until metal is etched. Flush with water, avoiding damage to adjacent areas; or wipe to a smooth finish, let dry, and paint. Follow paint manufacturer's instructions for undercoats and topcoats. Where rust is present apply one coat of Rustex to prep and etch the metal. Leave overnight, or until completely dry. Brush off any loose powder before painting.

#### WARNING: SEVERE EYE AND SKIN IRRITANT.

Contains Phosphoric Acid. In case of contact with eyes or skin, flush with water for 15 minutes. If irritation persists, seek medical attention. If swallowed, take large amounts of water. **Do not induce vomiting. Get medical attention.** 

#### KEEP OUT OF REACH OF CHILDREN.

Form: GDH-548 Rev.: 021916

1



## **TECHNICAL DATA**

## KRUD KUTTER® RUSTEX™ RUST CONVERTER

## PHYSICAL PROPERTIES

	RUSTEX RUST CONVERTER
Composition	Phosphoric Acid and other Proprietary Ingredients in a Water-based Solution
Color	Light Green
pH	1-2
voc	1%
Practical Coverage	32 ounces – 150 square feet
	1-Gallon – 600 square feet
Shelf Life	NA
Flash Point	Non-flammable Non-flammable
Caution!	WARNING: SEVERE EYE AND SKIN IRRITANT. Contains Phosphoric Acid. In case of contact with eyes or skin, flush with water for 15 minutes. If irritation persists, seek medical attention. If swallowed, take large amounts of water. Do not induce vomiting.  Get medical attention. KEEP OUT OF REACH OF CHILDREN.
Safety Information	For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Phone: 877•385•8155 www.rustoleum.com Form: GDH-548 Rev.: 021916