



INTERIOR SATIN ENAMEL PAINT

NO. 7050 ULTRA PURE WHITE®



PRODUCT INFORMATION

BEHR PREMIUM PLUS® Interior Satin Enamel Paint is a GREENGUARD® Gold certified 100% acrylic paint & primer in one that contains an antimicrobial agent to protect the surface of the paint film from mold & mildew. This versatile, easy-clean finish provides ultimate durability, exceptional hide and a pearl-like appearance. Formula is also low odor.

RECOMMENDED USES:

For properly prepared and primed or previously painted substrates including:

- Concrete
- Concrete Block/CMU
- Brick
- Plaster
- Drywall/Gypsum Board
- Wood
- Ferrous Metals
- Galvanized Steel
- Aluminum
- Other Non-Ferrous Metal
- Architectural Plastics

PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint Load:

- No. 7050 128 oz. / 2 oz.
- No. 7400 120 oz. / 10 oz.
- No. 7300 116 oz. / 14 oz.

Pre-mixed colors:

- No. 7012 Swiss Coffee
- No. 7052 White

Gloss: 15-25 @ 60°

Sheen: >35 @ 85°

Resin Type: 100% Acrylic Latex

Weight per Gallon: 10.7 lbs.

% Solids by Volume: 39%

% Solids by Weight: 51.5%

VOC: <5 g/L

Flash Point: N/A

Viscosity: 100-110 KU

Recommended Film Thickness:

- Wet: 6.4 mils / Dry: 2.3 mils @ 250 Sq. Ft./Gal.
- Wet: 2.6 mils / Dry: 1.4 mils @ 400 Sq. Ft./Gal.

Coverage: 250-400 Sq. Ft./Gal. depending on application method and substrate porosity. Does not include the loss of material from spraying.

APPLICATION:

Brush: Nylon/polyester

Roller:

- Smooth Surface:** 3/8" - 1/2" nap
- Rough Surface:** 1/2" - 3/4" nap

Airless Spray: At packaged consistency

Tip: .015" - .019"

Filter: 60 mesh

Thinning: (If required) No more than 1/2 pint of water per gallon.

Dry Time: @ 77° & 50% RH

Longer dry time may be required in cooler temperatures and higher humidity.

To Touch: 1 hour

To Recoat: 2 hours

Full Cure: 4 weeks

SURFACE PREPARATION:

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust and all other foreign substances.

New Drywall: All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating. **Previously Painted Drywall:** Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material. Let dry completely and sand smooth. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly before coating.

New Wood: Remove mill glaze with sand paper. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Previously Painted Wood: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to

COMPLIES WITH THE BELOW AS OF 12/1/2016

SCAQMD	YES	LEED v.4 ¹	YES
CARB	YES	MPI#	43,140,146
OTC	YES	MPI X-GREEN	43,140,146
LADCO	YES	GREENGUARD®	YES
AIM	YES	CHPS	YES
LEED v.3 (2009) ¹	YES	NAHB/ICC NGBS	YES

This coating conforms to USDA regulatory requirements for incidental food-contact materials intended for use on surfaces not in direct contact with food, such as walls, floors and ceilings.

¹Please see www.usgbc.org/LEED for additional details. GREENGUARD is a registered trademark of UL Company.

completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating.

Wood: WARNING! Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

New Plaster: New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize. **Previously Painted Plaster:** Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating. **Glossy Surfaces:** For maximum adhesion, sand the surface thoroughly before coating.

Stainblocking: After priming, test for stain bleed-through by applying the topcoat to a small section. If the stain bleeds through the topcoat, apply a second coat of primer and test again before top-coating the entire area. If bleeding continues, a longer dry time of the primer may be needed before top-coating.

Masonry: All masonry surfaces must be cured at least 30 days before painting. The pH must be 10.0 or lower prior to coating. Smooth masonry may require an adequate profile for adhesion. For all other smooth trowel concrete, create a profile using a product such as a muriatic acid etcher or with mechanical means. Remove all loose aggregate and debris.

Metals: Ferrous and Non-Ferrous Metals: All metals should be clean and free of any oils, rust, mill scale or other contaminants. All metals require sufficient "tooth" or





INTERIOR SATIN ENAMEL PAINT

NO. 7050 ULTRA PURE WHITE®

profile for optimum adhesion and therefore require some type of sanding, abrasion, or chemical etching. **Oil films:** (especially on new or non-ferrous metals) should be removed by scrubbing the surface with a detergent and water solution, and thoroughly rinsed. **Rust and Mill Scale:** Remove all rust and mill scale using sandpaper, steel wool, abrasive blasting, or other abrading methods. **Profile:** For best adhesion results, sand all metal surfaces (including new ones) with sandpaper, steel wool, or etch using a product such as a muriatic acid. Clean by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. All ferrous metals must be primed the same day it is cleaned to prevent rust.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact the National Lead Information Center at 1-800-424-LEAD or visit www.epa.gov/lead.

RECOMMENDED PRIMER/SYSTEMS:

PREVIOUSLY PAINTED SURFACES:

- Although BEHR PREMIUM PLUS® Paint is a paint & primer in one over most properly prepared surfaces, it is recommended for optimum performance to follow the primer recommendations provided below.

PROPERLY PREPARED NEW SURFACES:

Drywall:

- BEHR PREMIUM PLUS® Interior Drywall Primer & Sealer No. 73
For optimal enamel hold out, use BEHR PREMIUM PLUS® All-In-One Primer & Sealer No. 75.

Plaster:

- BEHR PREMIUM PLUS® All-In-One Primer & Sealer No. 75

Wood:

BEHR PREMIUM PLUS All-In-One Primer & Sealer No. 75

Tannin/Stainblocking:

BEHR PREMIUM PLUS All-In-One Primer & Sealer No. 75

Masonry:

- BEHR PREMIUM® Basement & Masonry Waterproofer No. 875
- BEHR PREMIUM PLUS All-In-one Primer & Sealer No. 75

Masonry with pH Levels up to 13.0:

- BEHR PREMIUM Basement & Masonry Waterproofer No. 875

Ferrous and Non-Ferrous Metals:

- BEHR PREMIUM PLUS All-In-one Primer & Sealer No. 75

TEST SPECIFICATIONS:

Scrubability:

ASTM D2486 Scrub > 2000 (no shim)

Flexibility:

ASTM D522, method B - Pass

CLEAN UP:

Clean all tools and equipment with clean water.
For disposal of empty containers and unused product, contact your household refuse collection service.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- Do not use on floors.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying too fast, whereas temperatures less than 50°F can cause slow drying or prevent proper film formation.
- Avoid heavy traffic for 24 hours.
- Allow four weeks before washing or cleaning for full cure.
- Shelf life under normal conditions is two years unopened.

GENERAL INFORMATION:



Warning! Causes eye and skin irritation. Wear protective clothing, gloves, eye, and face protection. Do not eat, drink, or smoke when using this product. Take off contaminated clothing and wash it before reuse. Wash hands thoroughly after handling. Dispose of unused contents, container and other contaminated wastes in accordance with local, state, federal and provincial regulations.

First aid: If in eyes: Rinse cautiously with water for several minutes and remove contacts if present and easy to do. Continue rinsing and get medical attention if eye irritation persists. **If on skin:** Wash with plenty of soap and water. **If swallowed:** Rinse mouth and get medical attention if you feel unwell.