



AquaTight™ Grout Additive

Instructions for use

Mixing:

1. Use in place of water for mixing grout. Do not mix with bleach.

When using sanded tile grout:

2. Pour one full 72 fl. oz. (2.1 L) bottle of AquaTight Additive into a clean, dry 5 gal. pail.
3. Add 25 lb. (11.3 kg) of sanded grout to the additive.
4. If additional liquid is required to achieve the desired consistency, up to a maximum of 2 fl. oz. (59 ml) of cool, clean water may be used.

When using unsanded tile grout:

2. Pour 49 fl. oz. (1.4 L) of AquaTight Additive into a clean, dry 5 gal. pail.
3. Add 10 lb. (4.5 kg) of unsanded grout to the additive.
4. If additional liquid is required to achieve the desired consistency, up to a maximum of 2 fl. oz. (59 ml) AquaTight Additive may be used.
5. Mix to a stiff, lump free consistency using a low speed drill. If using a mechanical mixer, do not exceed 150 rpm & avoid whipping air into the mixture.
6. Let stand for 10 minutes to give all ingredients time to slake. Remix and use.
7. Do not add more liquid or dry grout to the mix after slaking.

Application:

1. Follow manufacturer's instructions for grout installation.
2. Install grout when temperature is above 50°F (10°C).
3. For enhanced water beading, use AquaTight Additive instead of water for final grout cleaning.
4. Protect from traffic for 24 hours and water immersion or freezing for 7 days.

Shelf Life:

24 months from the date of manufacture when stored in the original, unopened container under cool, dry conditions and out of direct sunlight.

Clean Up:

Clean tools immediately by washing with water. Wash exposed skin with soap and water.



Nonfood Compounds
Program Listed (RX-2)
(Registration # 148968)