

# 398 ALL-WEATHER

HVAC

DUCT TAPE



- Backing:** Polyethylene Coated Cloth
- Adhesive:** Natural Rubber
- Liner:** N/A
- Specifications:** N/A
- Colors:** Silver, Black, White, Red
- Available Size:** 1.89 in x 60.1 yd x 11 mil  
(48 mm x 55 m x 279 µm)

## Applications

- Indoor/outdoor seal, patch, and bond
- Duct sealing and HVAC contractor applications
- Maintenance uses in manufacturing environments
- Hanging and sealing poly sheeting
- Challenging household maintenance and repair
- Bonding to difficult/rough surfaces

## Features

## Benefits

Natural Rubber Adhesive	<ul style="list-style-type: none"> <li>• Aggressive adhesion to rough surfaces</li> <li>• Superior holding power for hanging applications</li> <li>• Moisture-resistant</li> <li>• Excellent outdoor performance in all weather conditions</li> </ul>
Polyethylene Coated Cloth Backing	<ul style="list-style-type: none"> <li>• Durable and strong for outdoor uses</li> <li>• Clean, crisp, straight tear</li> <li>• Conforms well to irregular surfaces</li> <li>• Resists twisting and curling</li> </ul>
Multi-Color Assortment	<ul style="list-style-type: none"> <li>• Great for color coding uses</li> </ul>
Low VOC Content	<ul style="list-style-type: none"> <li>• Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED®</li> </ul>

## Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	11.0 mils	279 µm	ASTM D-1000
<b>Adhesion to Steel</b>	50 oz/in	5.47 N/cm	PSTC-101
<b>Tensile Strength</b>	23 lb/in	40.28 N/cm	ASTM D-1000
<b>Operating Temperature</b>	40 to 200 °F	4 to 93 °C	
<b>VOC Content</b>	< 1 g/L		
Recommended Storage Conditions: 60 - 80 °F at 40-60% RH			
Standard Shelf Life (at 25 °C): 36 months from date of manufacture			

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.