



**RUST-OLEUM® AMERICAN ACCENTS®
STONE SPRAYS**

DESCRIPTION AND USES

Rust-Oleum® American Accents® Stone is a unique textured finish for use on wood, metal, ceramics, glass & more. For use on interior surfaces only.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
238322	Stone Tuscan Rock
223324	Stone Mineral Brown
238325	Stone Canyon Moss
7990830	Stone Bleached Stone
7991830	Stone Black Granite
7992830	Stone Gray Stone
7994830	Stone Sienna Stone
7995830	Stone Pebble
285028	Stone Mica Travertine
285150	Stone Mica Slate
286729	Stone Mica Red Rock
238323	Stone Granite Stone

PRODUCT APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

PRIMING

Use of a Rust-Oleum primer provides excellent adhesion and hiding and is especially recommended for porous surfaces and bare wood and metal. For best hiding results, apply a basecoat of a color that blends well with the Stone finish.

APPLICATION

Shake can vigorously for one minute after mixing ball begins to rattle. Shake often during use. If mixing ball fails to rattle, **DO NOT STRIKE CAN.** Contact Rust-Oleum. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. The Stone finish will vary depending on how far away you spray. Keep the can in motion while spraying. Do not try to achieve total coverage in one coat. Apply one light coat first. Wait 15 minutes until paint starts to set, then apply a second coat. If additional coats are needed, wait 15 minutes between coats. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 3-4 hours and to handle in 5-6 hours. For objects exposed to moisture, apply Rust-Oleum Matte Clear top coat for optimal durability. Allow the final coat to dry for 4 hours before applying a clear top coat.

CLEAN-UP

When finished spraying, clear spray valve by turning can upside down and pushing spray button for 5 seconds. Clean up wet paint with xylol or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

<small>TRUSTED QUALITY SINCE 1921</small> RUST-OLEUM AMERICAN ACCENTS	TECHNICAL DATA AAC-06 RUST-OLEUM® AMERICAN ACCENTS® STONE SPRAYS
---	---

PHYSICAL PROPERTIES

		STONE SPRAYS
Resin Type		Water-based Acrylic
Pigment Type		Varies with color
Solvents		Acetone, Water
MIR		Maximum value of 1.05
Fill Weight		12 ounces
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		10-12 sq.ft./can (0.9-1.09 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	15 minutes
	Handle	30 minutes
	Recoat	At anytime
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.