


LITOELASTIC

LITOELASTIC • APPLICATION



1 Empty completely all the contents of the catalyst (B) onto the paste (A).



3 Mix using an electric drill equipped with mixing paddle (Never mix only by hand with a trowel). Scrape the walls of the bucket to eliminate all parts of non-catalysed product.



4 Apply the product with a notched trowel.



5 The tiles are laid on the adhesive applying a consistent pressure to ensure contact with the adhesive before its drying up which will occur after 50 minutes.



6 The joints between the tiles may be grouted after about 24 hours.



WATERPROOFING OF SURFACES AND GLUEING

To obtain the simultaneous waterproofing of the surface, you can proceed in two ways:

1 - Apply the product with a smooth trowel to a thickness of about 2 mm and apply an additional quantity of adhesive immediately after with the notched side of the trowel, leaving a continuous 1 mm thick layer of the product.



2 - Create a levelling of at least 1 mm of thickness. When the product is walkable (approx. 24 hours), then glue the ceramic tiles using a notched trowel.



LITOKOL®
HI-PERFORMANCE BUILDING PRODUCTS

Made In Italy

the
Tile Doctor

EXCLUSIVE DISTRIBUTOR FOR USA
Tile Doctor
www.TileDoctor.com
877-TileDoc (845-3362)