

SuperArc® L-56®

Mild Steel, Copper Coated • AWS ER70S-6 & EH11K

Key Features

- ▶ High levels of manganese and silicon deoxidizers tolerate medium to heavy mill scale surfaces
- ▶ Excellent toe-wetting provides optimal bead appearance
- ▶ Copper coated for long contact tip life
- ▶ Supports short-circuiting, globular, axial spray and pulsed spray transfer
- ▶ MicroGuard® Ultra provides superior feeding and arc stability

Typical Applications

- ▶ Medium to heavy mill scale base material
- ▶ Automotive repair
- ▶ Sheet metal to 380-485 MPa (55-70 ksi) yield strength material
- ▶ Robotic or hard automation
- ▶ Structural steel

Conformances

AWS A5.18/A5.18M: 2005	ER70S-6
ASME SFA-A5.18:	ER70S-6
AWS A5.17/A5.17M: 1997	EH11K
ABS:	3YSA
Lloyd's Register:	3YS H15
DNV Grade:	III YMS
CWB/CSA W48-06:	ER49S-6
DB:	EN 440 G3Si1
TUV:	EN 440 G3Si1
EN ISO 14341-B:	G 49A 3 C S6
MIL-E-23765/1:	MIL-70S-6

Welding Positions

All

Shielding Gas

100% CO₂ 95-98% Argon / Balance O₂
75-95% Argon / Balance CO₂ Flow Rate: 30-50 CFH

DIAMETERS / PACKAGING

Diameter in (mm)	2 lb (1 kg) Plastic Spool 10 lb (4.5 kg) Master Carton	12.5 lb (5.7 kg) Plastic Spool	33 lb (15 kg) Plastic Spool	33 lb (15 kg) Steel Spool	44 lb (20 kg) Steel Spool
0.025 (0.6)	ED030583	ED015790			
0.030 (0.8)	ED030631	ED023334	ED032926		
0.035 (0.9)	ED030632	ED028676	ED032927	ED031411	ED025945
0.045 (1.1)		ED029042	ED032928	ED031412	ED025946
Diameter in (mm)	44 lb (20 kg) Fiber Spool	60 lb (27.2 kg) Coil	60 lb (27.2 kg) Fiber Spool	250 lb (113.4 kg) Accu-Trak® Drum	500 lb (227 kg) Accu-Trak® Drum
0.030 (0.8)			ED021275	ED029914	ED030771
0.035 (0.9)	ED021274				ED021056
0.040 (1.0)	ED027384				ED031937
0.045 (1.1)	ED021276		ED021277	ED029915	ED020532
0.052 (1.3)	ED021278		ED021279	ED029916	ED020533
1/16 (1.6)		ED011666			ED029225
Diameter in (mm)	500 lb (227 kg) Accu-Pak® Box	900 lb (408 kg) Accu-Pak® Box	1000 lb (454 kg) Accu-Trak® Drum	1000 lb (454 kg) Accu-Pak® Box	1000 lb (454 kg) Precise-Trak® Reel
0.035 (0.9)	ED032904	ED032847	ED028827		ED033271
0.040 (1.0)			ED031032		
0.045 (1.1)	ED032906		ED028828	ED032849	ED031616
0.052 (1.3)	ED032907		ED029084	ED032850	ED031617
1/16 (1.6)			ED029085	ED032851	

WIRE COMPOSITION – As Required per AWS A5.18/A5.18M: 2005

	%C	%Mn	%Si	%S	%P
Requirements - AWS ER70S-6	0.06-0.15	1.40-1.85	0.80-1.15	0.035 max.	0.025 max.
Typical Results ⁽³⁾	0.08-0.09	1.42-1.65	0.81-0.87	0.006-0.010	0.004-0.010
	%Cr	%Ni	%Mo	%V	%Cu (Total) ⁽⁴⁾
Requirements - AWS ER70S-6	0.15 max.	0.15 max.	0.15 max.	0.03 max.	0.50 max.
Typical Results ⁽³⁾	0.01-0.05	≤ 0.04	≤ 0.01	< 0.01	0.17-0.22

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.18/A5.18M: 2005

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft•lbf)	
				@ -29°C (-20°F)	@ -40°C (-40°F)
Requirements - AWS ER70S-6					
As-Welded with 100% CO ₂	400 (58) min.	485 (70) min.	22 min.	27 (20) min.	Not Specified
MIL-70S-6 per MIL-E-23765/1					
As-Welded with CO ₂ and 98% Ar/2% O ₂	380-550 (55-80)	485 (70) min.	22 min.	Not Specified	Not Specified
MIL-70S-6 per MIL-E-23765/1					
Stress Relieved 1 hr. @ 621°C (1150° F) with CO ₂ and 98% Ar/2% O ₂	360 (52) min.	485 (70) min.	26 min.	27 (20) min.	Not Specified
Typical Results⁽³⁾					
As-Welded with 100% CO ₂	440 (64)	560 (81)	29	71 (52)	61 (45)
Stress Relieved 1 hr. @ 621°C (1150°F)	395 (57)	510 (74)	29	95 (70)	68 (50)
As-Welded with 75% Ar/25% CO ₂	460 (67)	565 (82)	27	82 (60)	72 (53)
Stress Relieved 1 hr. @ 621°C (1150°F)	415 (60)	540 (78)	31	140 (103)	122 (90)
As-Welded with 90% Ar/10% CO ₂	470 (68)	580 (84)	28	119 (88)	78 (57)
Stress Relieved 1 hr. @ 621°C (1150°F)	440 (64)	550 (80)	32	183 (135)	156 (115)
As-Welded with 98% Ar/2% O ₂	455 (66)	565 (82)	27	122 (90)	108 (80)
Stress Relieved 1 hr. @ 621°C (1150°F)	415 (60)	545 (79)	34	190 (140)	176 (130)

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁶⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)
0.025 in (0.6 mm), DC+					
Short Circuit Transfer 100% CO ₂	9-12 (3/8-1/2)	2.5 (100)	17	35	0.4 (0.9)
		6.4 (250)	19	80	0.9 (2.0)
0.030 in (0.8 mm), DC+					
Short Circuit Transfer 100% CO ₂	9-12 (3/8-1/2)	1.9 (75)	17	35	0.4 (0.9)
		3.8 (150)	18	70	0.8 (1.8)
		7.6 (300)	22	130	1.6 (3.6)
0.035 in (0.9 mm), DC+					
Short Circuit Transfer 100% CO ₂ ⁽⁶⁾	9-12 (3/8-1/2)	2.5 (100)	18	80	0.7 (1.6)
		3.8 (150)	19	120	1.1 (2.4)
		6.4 (250)	22	175	1.8 (4.0)
Spray Transfer 90% Ar/10% CO ₂	12-19 (1/2-3/4)	9.5 (375)	23	195	2.7 (6.0)
		12.7 (500)	29	230	3.6 (8.0)
		15.2 (600)	30	275	4.4 (9.6)
0.045 in (1.1 mm), DC+					
Short Circuit Transfer 100% CO ₂ ⁽⁶⁾	12-19 (1/2-3/4)	3.2 (125)	19	145	1.5 (3.4)
		3.8 (150)	20	165	1.8 (4.0)
		5.1 (200)	21	200	2.5 (5.4)
Spray Transfer 90% Ar/10% CO ₂	12-19 (1/2-3/4)	8.9 (350)	27	285	4.2 (9.2)
		12.1 (475)	30	335	5.7 (12.5)
		12.7 (500)	30	340	6.0 (13.2)
0.052 in (1.3 mm), DC+					
Spray Transfer 90% Ar/10% CO ₂	12-19 (1/2-3/4)	7.6 (300)	30	300	4.8 (10.7)
		8.1 (320)	30	320	5.2 (11.5)
		12.3 (485)	32	430	7.8 (17.1)
1/16 in (1.6 mm), DC+					
Spray Transfer 90% Ar/10% CO ₂	12-25 (1/2-1)	5.3 (210)	27	325	4.8 (10.7)
		6.0 (235)	28	350	5.4 (12.0)
		7.4 (290)	29	430	6.7 (14.8)

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer below. ⁽⁴⁾Copper due to any coating on the electrode plus the copper content of the filler metal itself, shall not exceed the stated 0.50% max. ⁽⁵⁾CTWD (Contact Tip to Work Distance). Subtract 1/4 in (6.4 mm) to calculate Electrical Stickout. ⁽⁶⁾Procedures in these areas are procedures for short circuiting mode using 100% CO₂. When using 75% Argon, 25% CO₂ for short circuit transfer, reduce voltage by 1 to 2 volts.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.