



**CHALKED  
ULTRA MATTE PAINT**

**DESCRIPTION AND USES**

Rust-Oleum® Chalked Ultra Matte Paint is formulated as an ultra matte finish with excellent coverage and adhesion on furniture and home décor. Chalked Ultra Matte paint provides one coat coverage on most surfaces without special surface preparation or priming. It can be painted or distressed. It is suitable for use on wood, metal, ceramic, glass, canvas and more. **For interior use only.**

**PRODUCTS**

SKU	Description
285139	Serenity Blue
285140	Linen White
285141	Country Gray
285142	Blush Pink
285143	Aged Gray
285144	Charcoal

**PAINTING CONDITIONS**

Use in a well ventilated area such as an open garage. Apply when temperature is between 50 and 90°F (10-32°C) and humidity is below 85% to ensure proper drying.

**PRODUCT APPLICATION**

**SURFACE PREPARATION**

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with soap and water and let dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Remove any wax by lightly wiping the surface with mineral spirits.

**WARNING:** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRODUCT APPLICATION (cont.)**

**PRIMING**

Priming is not required for most surfaces. For excellent coverage, use of a Rust-Oleum primer can be used on surfaces such as bare wood and treated wood. The finish coat can be applied 2 hours after applying the primer. Recommended primers include:

- Painter's Touch 1908502 Flat Gray
- Painter's Touch 224430T Flat White

**APPLICATION**

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Stir thoroughly to ensure any settled pigment is re-dispersed. Do not shake the can. Thinning is not required. In hot, dry conditions, thin with up to 2 ounces of fresh water per quart to extend the dry time. Avoid painting in direct sunlight or on hot surfaces.

Use a high quality synthetic brush. Roller application is not recommended. Avoid excessive brushing as this will reduce film thickness and protection. Use light even brush strokes to ensure even flow and the smoothest finish.

**DRY & RECOAT**

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 30 minutes, to handle in 1 hour and can be recoated after 2-4 hours. The finish coat is fully dry in 2-4 hours. Rust-Oleum Chalked Clear Protective Topcoat can be applied for added protection. Apply according to the label instructions.

**DISTRESSING**

This paint can be distressed if desired. To distress the surface, lightly sand the surface with fine to medium grit sandpaper or a sanding sponge. Wait 2 hours before sanding or distressing.

**CLEAN-UP**

Clean brush and other and application tools with soap and water.

**TECHNICAL DATA****CHALKED ULTRA MATTE PAINT****PHYSICAL PROPERTIES**

		CHALKED ULTRA MATTE PAINT
<b>Resin Type</b>		Acrylic
<b>Pigment Type</b>		Titanium Dioxide and Inerts
<b>Solvents</b>		Water and Glycol Ethers
<b>Weight</b>	<b>Per Gallon</b>	13.1-13.8 lbs.
	<b>Per Liter</b>	1.6-1.65 kg
<b>Solids</b>	<b>By Weight</b>	61.0-64.0%
	<b>By Volume</b>	39.0-40.0%
<b>Volatile Organic Compounds</b>		<75 g/l (0.62 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		1.0-2.0 mils (25-50 $\mu$ )
<b>Wet Film to Achieve DFT</b>		3.0-5.0 mils (75-125 $\mu$ )
<b>Practical Coverage at Recommended DFT</b>		110-150 sq.ft./qt. (2.7-3.7 m <sup>2</sup> /l)
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Touch</b>	30 minutes
	<b>Handle</b>	1-2 hours
	<b>Recoat</b>	2-4 hours
	<b>Topcoat</b>	2-4 hours
<b>Shelf Life</b>		3 years
<b>Flash Point</b>		>200°F (93°C)
<b>Safety Information</b>		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
11 Hawthorn Parkway  
Vernon Hills, Illinois 60061  
An RPM Company

Phone: 877-385-8155  
www.rustoleum.com

Form: GDH-772  
Rev.: 081915